



Functional fillers


Neuburg
Siliceous Earth

[Product information](#)

HOFFMANN
MINERAL®

We supply material for good ideas

Products	3
Morphology	4
Separation process	6
Particle size distribution	8
Sillitin Sillikolloid Silfit	
Color neutrality	9
Sillitin Sillikolloid Silfit	
Product characteristics	10
Sillitin Sillikolloid	
Product characteristics	12
Puriss	
Product characteristics	14
Aktisil	
CIELAB color values and functionalization	16
Silfit Aktifit	
Product characteristics	18
Silfit Aktifit	
Packaging	20
Testing methods	22



Sillitin | Sillikolloid

Standard products (natural, untreated fillers). Differ in brightness and particle size distribution.

Puriss

Created by a downstream process. The extremely low residue > 40 µm particles is reduced even more and the dispersion properties are improved.

Aktisil


Surface-treated products. Neuburg Siliceous Earth treated with additives.

Silfit

Calcined products based on Sillitin. A downstream thermal process gives the product additional application advantages as a functional filler.


Aktifit

An activated Silfit produced through surface treatment with special additives.



Classic Neuburg Siliceous Earth is a natural combination of corpuscular Neuburg Silica and lamellar kaolinite: a loose mixture impossible to separate by physical methods. As a result of natural aging, the silica portion exhibits a round grain shape and consists of aggregated cryptocrystalline primary particles of about 200 nm diameter. Such a unique structure is responsible for a relatively high specific surface area and oil absorption, which result, besides rheological activity, also in a whole range of application properties.

Our calcined products Silfit and Aktifit are based on the standard product Sillitin Z 86. A thermal process is used to expel the crystalline water in the kaolinite portion and new mineral phases are formed practically amorphous. The silica portion remains inert at the temperature used. The resulting products have an outstandingly high degree of white and color neutrality.




Basically speaking, our entire production process is a process of separation – only about 30% of the raw earth extracted is a usable fine product.

A particularly structure-conserving process separates the fine product from sand, sundry stones and rocks. In the first step, the raw material is dispersed in water and thus separated from gravel fractions. This is followed by the hydrocyclone unit which


separates the sand fractions and divides the fine particles into different particle sizes. The slurry obtained is then concentrated and the water removed in filter presses. Finally, the natural gas powered turbine dryers remove the remaining moisture. The material is then pulverized and stored for further processing.

The particle size distribution, color value graphs and overview tables on the following pages show the physical properties and chemical composition of Neuburg Siliceous Earth. The most significant differentiating characteristics are particle size distribution and color neutrality.

Neuburg Siliceous Earth is available in four different particle fractions, identified by the letters V, N, Z and P.




In addition, classic Neuburg Siliceous Earth is available in different shades and colors ranging from yellow to off-white to white depending on the particle size distribution. This color neutrality is expressed in numbers.



Puriss

- The extremely low residue of > 40 µm is significantly reduced even more
- Reduction of wear when processing through optimum dispersion in low viscosity compounds
- puriss products are the #1 choice for extremely high requirements in terms of dispersion performance and surface quality for application in elastomers and thermoplastic elastomers:
 - low viscosity compounds with high dose of plasticizer
 - extremely thin-walled products like membranes
 - printing roller coverings, printing stencils, offset printing blankets
 - low durometer automotive profiles with Class A surface quality

Stirred with blade mixer 1200 rpm, 20% filler concentration, grain size (Hegman gauge) ≤ 20 µm.










Product characteristic	Unit	Sillitin N 85 puriss	Sillitin Z 86 puriss	Sillitin Z 89 puriss	Sillikolloid P 87 puriss
Color values	L*	93.5	94.0	96.1	94.5
	a*	1.0	1.0	0.2	0.9
	b*	9.0	9.5	4.2	9.0
Particle size	D ₅₀	3.0	1.9	2.1	1.5
	D ₉₇	16	9	9.5	6
Residue > 40 µm	mg/kg	8	8	8	8
Volatile matter at 105 °C	%	0.5	0.5	0.5	0.5
pH value		8.7	8.7	8.7	8.7
Density	g/cm ³	2.6	2.6	2.6	2.6
Bulk density	g/cm ³	0.28	0.23	0.20	0.20
Tamped density	g/cm ³	0.48	0.37	0.34	0.34
Oil absorption	g/100g	45	55	55	55
Hardness silica/kaolinite		7/2.5	7/2.5	7/2.5	7/2.5
	Abrasivity	mg	35	30	30
Refractive index n		1.55	1.55	1.55	1.55
Water solubility	%	< 0.5	< 0.5	< 0.5	< 0.5
Acid solubility	%	< 1	< 1	< 1	< 1
Dispersion time in ester plasticizer	min	3	7	7	8
Chemical analysis:					
SiO ₂	%	84	82	82	80
Al ₂ O ₃	%	10	12	12	14
Fe ₂ O ₃	%	< 1	< 1	< 1	< 1
Mineralogical composition:					
Neuburg Silica	%	65	60	60	55
Kaolinite	%	20	25	25	30
Amorphous mineral phases	%	10	10	10	10
Other minerals	%	5	5	5	5

The values shown in the table are to be considered as guide values only. Material specifications for each product are binding and are available on our website www.hoffmann-mineral.com.

Aktisil

These special fillers are made by treating the surface of Neuburg Siliceous Earth with additives.


Product characteristic	Unit	 Aktisil AM	 Aktisil MAM-R	 Aktisil PF 216	 Aktisil PF 777	 Aktisil Q	 Aktisil VM 56	 Aktisil VM 56/89
Basic material Sillitin		Z 86	V 85	Z 86	Z 86	V 90 ¹	Z 86	Z 89
Functionalization		Amino	Methacrylic	Tetrasulfane	Alkyl	Methacrylic	Vinyl	Vinyl
Color values	L* a* b*	94.0 1.0 10.0	93.0 1.0 9.0	94.0 1.0 10.0	93.8 1.0 10.0	94.5 0.3 4.0	94.0 1.0 10.0	96.0 0.2 3.7
Particle size	D ₅₀ D ₉₇	μm μm	2.4 5.0 12	2.4 5.0 12	2.4 5.0 12	5.0 18	2.4 5.0 12	2.4 5.0 12
Residue	> 40 μm	mg/kg	30	30	15	20	25	15
Volatile matter at 105 °C	%		0.3	0.2	0.3	0.3	0.3	0.5
Density	g/cm ³		2.6	2.6	2.6	2.6	2.6	2.6
Bulk density	g/cm ³		0.22	0.35	0.25	0.25	0.45	0.25
Spec. surface area (BET)	m ² /g		10	9	10	9	6	9
Oil absorption	g/100 g		60	45	60	40	43	45
Water absorption	ml/g		not specified	0.9	≤ 0.1	≤ 0.1	0.5	not specified
Reactive			✓	✓	✓	✓	✓	✓
Hydrophobic					✓	✓		







¹ internal product quality

The values shown in the table are to be considered as guide values only. Material specifications for each product are binding and are available on our website www.hoffmann-mineral.com.

Silfit | Aktifit

With regard to the CIELAB Color Values L^* , a^* and in particular b^* , the calcined products are significantly brighter and more color neutral than the basic material.



Product characteristic	Unit						
		Silfit Z 91	Aktifit AM	Aktifit PF 111	Aktifit PF 115	Aktifit Q	Aktifit VM
Basic material		Sillit Z 86	Silfit Z 91	Silfit Z 91	Silfit Z 91	Silfit Z 91	Silfit Z 91
Functionalization		–	Amino	Alkyl	Amino	Methacrylic	Vinyl
Color values							
L*		96.5	96.3	96.3	95.7	96.3	96.3
a*		–0.2	–0.1	–0.1	0	–0.1	–0.1
b*		1.0	1.1	1.0	1.0	1.1	1.0
Particle size							
D ₅₀	µm	2.1	2.3	2.3	2.3	2.3	2.3
D ₉₇	µm	9.5	11	11	11	11	11
Residue > 40 µm	mg/kg	10	10	10	10	20	10
Volatile matter at 105 °C	%	0.2	0.2	0.2	0.1	0.2	0.1
Density	g/cm ³	2.6	2.6	2.6	2.6	2.6	2.6
Bulk density	g/cm ³	0.3	0.31	0.35	0.35	0.35	0.37
Tamped density	g/cm ³	0.55	0.55	0.65	0.7	0.6	0.7
Spec. surface area (BET)	m ² /g	10	9	9	9	8	10
Oil absorption	g/100 g	65	65	55	60	65	65
Silica hardness/calced kaolinite		7/4.5	7/4.5	7/4.5	7/4.5	7/4.5	7/4.5
Refractive index n		1.55	1.55	1.55	1.55	1.55	1.55
Water solubility	%	< 0.5	< 0.5	not applicable	not applicable	not applicable	not applicable
Acid solubility	%	< 1	< 1	not applicable	< 1	not applicable	not applicable
pH value		6.5	not applicable	not applicable	not applicable	not applicable	not applicable
Water absorption	ml/g	not specified	not specified	≤ 0.1	≤ 0.1	≤ 0.1	≤ 0.1
Chemical analysis:							
SiO ₂	%	86	86	86	86	86	86
Al ₂ O ₃	%	13	13	13	13	13	13
Fe ₂ O ₃	%	< 1	< 1	< 1	< 1	< 1	< 1
Mineralogical composition:							
Neuburg Silica	%	60	60	60	60	60	60
Calcined kaolinite	%	40	40	40	40	40	40
Equilibrium moisture content at 25 °C and 50% relative humidity	%	0.12	0.11	0.07	0.04	0.04	0.05
and 80% relative humidity	%	0.22	0.29	0.10	0.06	0.06	0.07
and 90% relative humidity	%	0.54	0.55	0.13	0.07	0.07	0.08
Reactive			✓		✓	✓	✓
Hydrophobic				✓	✓	✓	✓

The values shown in the table are to be considered as guide values only. Material specifications for each product are binding and are available on our website www.hoffmann-mineral.com.

EINECS no.: 310-127-6
 TSCA no.: 7631-86-9 (silica),
 92704-41-1 (kaolin, calcined)



CAS no.: 1214268-39-9 (Siliceous Earth, calcined)
 CAS no.: 7631-86-9 (silica),
 92704-41-1 (kaolin, calcined)

Product	Paper bag	EVA-bag	Big Bag Type 1/ Type 2/Type 3	Bulk
 Sillitin V 85	25 kg	5 to 20 kg	≤ 750/850/1200 kg	≤ 25 t
 Sillitin V 88	25 kg	5 to 20 kg	≤ 750/850/1200 kg	≤ 25 t
 Sillitin N 75	25 kg	5 to 20 kg	≤ 750/850/1200 kg	≤ 25 t
 Sillitin N 85	25 kg	5 to 20 kg	≤ 750/850/1200 kg	≤ 25 t
 Sillitin N 87	25 kg	5 to 20 kg	≤ 750/850/1200 kg	≤ 25 t
 Sillitin Z 86	25 kg	5 to 20 kg	≤ 600/750/1000 kg	≤ 22 t
 Sillitin Z 89	25 kg	5 to 20 kg	≤ 550/700/900 kg	≤ 22 t





Sillikolloid


 Sillikolloid P 87	25 kg	5 to 15 kg	≤ 550/700/900 kg	≤ 22 t
---	-------	------------	------------------	--------

Puriss






 Sillitin puriss	25 kg	–	–	–
 Sillikolloid P 87 puriss	20 kg	–	–	–

Aktisil

 Aktisil AM	25 kg	5 to 20 kg	≤ 550/700/900 kg	–
 Aktisil MAM-R	25 kg	5 to 20 kg	≤ 550/700/900 kg	–
 Aktisil PF 216	25 kg	10 to 20 kg	≤ 550/700/900 kg	–
 Aktisil PF 777	25 kg	5 to 20 kg	≤ 550/700/900 kg	–
 Aktisil Q	25 kg	5 to 20 kg	≤ 550/700/900 kg	–
 Aktisil VM 56	25 kg	5 to 20 kg	≤ 550/700/900 kg	≤ 24 t
 Aktisil VM 56/89	25 kg	5 to 20 kg	≤ 550/700/900 kg	–

Product	Paper bag	EVA-bag	Big Bag Type 1/ Type 2/Type 3	Bulk
 Silfit Z 91	25 kg	10 to 20 kg	≤ 600/750/900 kg	on request

Aktifit

 Aktifit AM	25 kg	on request	≤ 600/750/900 kg	on request
 Aktifit PF 111	25 kg	on request	on request	–
 Aktifit PF 115	25 kg	on request	on request	–
 Aktifit Q	25 kg	on request	on request	–
 Aktifit VM	25 kg	on request	≤ 550/900/– kg	–

Special packaging and sizes are available on request.

Product characteristic	Testing method
Color values L* a* b*	acc. to CIELAB
Particle size D ₅₀ D ₉₇	acc. to ISO 13320
Residue > 40 µm	acc. to DIN EN ISO 787 part 18
Volatile matter at 105 °C	acc. to DIN EN ISO 787 part 2
Density Bulk density Tamped density	acc. to DIN EN ISO 787 part 10 acc. to DIN ISO 903-1976 acc. to DIN EN ISO 787 part 11
Spec. surface area (BET) Oil absorption	acc. to DIN ISO 9277 acc. to DIN EN ISO 787 part 5
Water absorption	acc. to Baumann
Hardness silica/kaolinite Abrasivity	acc. to Mohs acc. to Einlehner
Refractive index n	sin α/sin β
Water solubility Acid solubility	acc. to DIN EN ISO 787 part 3 acc. to DIN 53 770 (0.1 N HCl)
pH value	acc. to DIN EN ISO 787 part 9
Chemical analysis: SiO ₂ Al ₂ O ₃ Fe ₂ O ₃	acc. to DIN 51001 (RFA)
Mineralogical composition: Corpuscular silica Amorphous mineral phases Kaolinite and other minerals	based on X-ray diffraction pattern analysis combined with Rietveld
Equilibrium moisture content at 25 °C and 50% relative humidity and 80% relative humidity and 90% relative humidity	following DIN 66138
Dispersion time in ester plasticizer	UGR-PV/PT/67

To find out more about the applications, close the brochure now and turn it so that the application section is in front of you.



Neuburg
Siliceous Earth
Product information

Elastomers
TPE
Thermoplastics
Applications

Functional fillers

Elastomers
TPE
Thermoplastics

Applications



Image source

Application	Page	Source
Car body seals, solid	12	2018 tomas devera photo/Shutterstock
EPDM profiles, foamed	13	Hoffmann Mineral GmbH
Direct glazing of fixed side windows	13	PICTURE-SERVICE
Molded gaskets, o-rings and radial shaft seals	14	KACO GmbH & Co. Kg
Radiator hoses	16	Kenneth Cheung
HCR Silicone turbocharger hoses	17	Sjoerd van der Wal/istockphoto.com
Urea-resistant EPDM gaskets and hoses	17	Deutz AG
Air intake hoses EPDM	18	Thomas Boellinghaus
Timing belts	18	FRANK HOFFMANN fm-fotodesign
Conveyor belt skim compounds	19	Thomas Boellinghaus
Elastomer-metal composites	19	Siegi – Fotolia
Roller coverings and printing blankets	20	zefart/stock.adobe.com
Washing machine gaskets and hoses	21	nosorogua/stock.adobe.com
Hydraulic and fuel hoses, oil-resistant hoses in general	22	ContiTech AG
Diaphragms for expansion vessels	23	nikkytok/Shutterstock
Cable sheaths, cable insulation	24	demarco/stock.adobe.com
Medium- and high voltage cable insulations	26	Nneirda/stock.adobe.com
High voltage isolators	27	Victor/stock.adobe.com
Capacitor gaskets	28	Sascha Wilsrecht/stock.adobe.com
Floor coverings	29	Elmar Witt/nora
Roofing membranes	29	aboutmomentsimages/stock.adobe.com
Anti-corrosion lining	30	Hoffmann Mineral GmbH
Building profiles (window and façade sealing)	31	JFL Photography/stock.adobe.com
Solar panel tubes for swimming pools	32	Ba_peuceta
Sealing profiles for road and tunnel construction	33	svedoliver – Fotolia
Sealing tape	33	Ruslan Sidorov/istockphoto.com
FKM Compounds	34	Edler von Rabenstein – Fotolia
Silicone rubber compounds	36	J and S Photography – Fotolia
Poatable water seals peroxide cross-linked	37	Svetlly/stock.adobe.com
Pharmaceutical closures	38	Gino Santa Maria
Food contact materials	38	Arina P Habich/shutterstock.com
Shoe components	39	Fotodesign Märzinger
Solid tires and spinning cot	39	wiha3/stock.adobe.com
Windshield water guide trim, SEBS compound on PP core in injection molding process	41	Hoffmann Mineral GmbH
Pickup truck liners, SEBS-PE compound	42	Danylo Samiilenko
Packaging seals like screw cap seals for acidic contents on a SEBS basis	42	callatis/Shutterstock
Housings and impact resistant molded parts, PA 6 and PA 66	46	Hoffmann Mineral GmbH
Polyphenylene sulfide (PPS)	46	Daniel Strautmman/stock.adobe.com
Scratch-resistant PP co-polymer compounds for automotive interior trim	47	sarki66/stock.adobe.com
3D printing, filament printing of ABS, FFF process	48	Grafner/istockphoto
Transport packaging for wafer canister, HDPE	48	S.P.S. Vertriebs GmbH
Polybutylene terephthalate (PBT)	49	BASF – Leistungshalbleitermodule von SEMIKRON aus Ultradur® von BASF
Polycarbonate (PC)	49	Kenishirotie/istockphoto
Wood-plastic composites (WPC), handles, extruded profiles	50	Alterfalter – Fotolia
Polyketon (PK)	50	Ing. Gerhard Fildan GesmbH
Films with anti-blocking, packaging and technical films	54	PRILL Mediendesign – Fotolia
Low melting point films with high EVA content	55	Hoffmann Mineral GmbH
Matting of TPU-films	56	Shutterstock (163330496)
Greenhouse film with IR barrier	57	kasparart – stock.adobe.com

EVM-11/06.2024/06105980

Contents

Advantages in elastomers	4
Selection criteria in elastomers Sillitin Sillikolloid Silfit	6
Selection criteria in elastomers Aktisil Aktifit	8
Applications in elastomers Aktisil Aktifit	10
Advantages and product recommendation Automotive Machine and equipment construction Cable and electrical industry Construction industry Other applications	12 19 24 29 34
Advantages in TPE	40
Advantages and product recommendation TPE	41
Advantages in thermoplastic molded parts	43
Selection criteria for thermoplastic molded parts Aktifit	44
Advantages and product recommendation Thermoplastic molded parts	46
Advantages in thermoplastic films	51
Selection criteria for thermoplastic films Sillitin Aktifit Silfit	52
Advantages and product recommendation Thermoplastic films	54
Publisher: HOFFMANN MINERAL GmbH Muenchener Strasse 75 86633 Neuburg a. d. Donau Germany Phone: +49 8431 53-0 E-Mail: info@hoffmann-mineral.com www.hoffmann-mineral.com	

Advantages in elastomers

Properties of Neuburg Siliceous Earth

Advantages for users




easily and rapidly mixed in, very good dispersion properties	> short mixing times, no agglomerates
high degree of filling	> low compound costs
good rheology	> molds with high number of cavities
good extrusion properties, good calendering properties	> high haul-off speeds with good surface quality for high quality extrusions and sheets, cost reduction through no or low need for auxiliary processing aids
matting effect	> high quality appearance with satin finish of black profiles
no negative influence on cure rate, good thermal conductivity	> short vulcanization time, high haul-off speed for continuous vulcanization
excellent surface	> visually perfect articles, few rejects
low tension and compression set	> excellent sealing properties
high electrical resistivity	> insulation with low loss
favorable aging properties	> long service life, cost reduction through low need for anti-aging agents
superior chemical resistance	> high resistance against aggressive media
high purity	> can be used in pharmaceutical articles and food contact materials
very low CO ₂ -footprint	> reduction of product carbon footprint of rubber compounds

Properties of Calcined Neuburg Siliceous Earth

Advantages for users













low moisture content, low moisture absorption	> lower risk of blistering for pressureless vulcanization
lowest chloride content	> prevention of corrosion e.g. at washing machine gaskets
very high brightness and color neutrality	> for white products without yellowness, less need for white pigments like titanium dioxide
optimum dispersion properties even in critical compounds, comparable with puriss products	> short mixing times, no agglomerates
avoids mold fouling/deposits on dies caused by filler	> high productivity and low costs thanks to reduction of stoppages for cleaning and prevention of waste
very fine cell structure in sponge and microcellular rubber	> high quality sponge and expanded rubber products
low dielectric loss in high voltage insulation	> reduced energy losses in electric power transmission
potential for lower compression set	> improved long-term sealing effect, for greater flexibility in creating recipes
potential for improved oil resistance	> combined with the very low compression set for meeting high demands for sealing
very low CO ₂ -footprint	> reduction of product carbon footprint of rubber compounds

Sillitin | Sillikolloid | Silfit

	 Sillitin V 85	 Sillitin V 88	 Sillitin N 75	 Sillitin N 85	 Sillitin N 87	 Sillitin Z 86	 Sillitin Z 89	 Silfit Z 91	 Sillikolloid P 87
Color neutrality	● ●	● ● ● ● ● ●	●	● ●	● ● ● ●	● ●	● ● ● ● ● ●	● ● ● ● ● ● ● ●	● ●
Extrusion	Profile quality, edge smoothness of complex profiles	●	●	● ● ● ●	● ●	● ●	● ● ● ●	● ● ● ● ○	● ● ● ● ● ●
	Collapse resistance	●	●	● ● ● ●	● ●	● ●	● ● ● ●	● ● ● ●	● ● ● ● ● ●
	Matting effect	● ● ● ● ● ●	● ● ● ● ● ●	● ● ● ●	● ● ● ●	● ● ● ●	● ●	● ●	●
Viscosity	●	●	● ● ● ●	● ●	● ●	● ● ● ●	● ● ● ●	● ● ● ● ○	● ● ● ● ● ●
Tensile strength	●	●	● ● ● ●	● ●	● ●	● ● ● ●	● ● ● ●	● ● ● ●	● ● ● ● ● ●
Tear resistance	●	●	● ● ● ●	● ●	● ●	● ● ● ●	● ● ● ●	● ● ● ●	● ● ● ● ● ●
Compression set	●	●	● ● ● ●	● ●	● ●	● ● ● ●	● ● ● ●	● ● ○	● ● ● ● ● ●
Rebound elasticity	● ● ● ● ● ●	● ● ● ● ● ●	● ● ● ●	● ● ● ●	● ● ● ●	● ●	● ●	● ●	●
Abrasion loss	● ● ● ● ● ●	● ● ● ● ● ●	● ●	● ● ● ●	● ● ● ●	● ●	● ●	● ●	●

Characteristic: respectively ● = low ● ● ● ● ● ● ● ● = high optimum

Aktisil | Aktifit

Product	Basic material	Functionalization	Sulphur/sulphur donors	Metal oxide	Resin, IIR	Peroxide, radiation	NR, SBR, BR, IR, NBR, HNBR (partly hydrogenated), CR, IIR, CIIR, BIIR	HNBR (fully hydrogenated) CM, CSM, EPM, EVM	EPDM	FKM, ACM, AEM (Vamac®)	Silicone compounds	PU-elastomers
 Aktisil AM	Sillitin Z 86	Amino	●	●		●	●	●	●	●		●
 Aktisil MAM-R	Sillitin V 85	Methacrylic			●	●	●	●	●			
 Aktisil PF 216	Sillitin Z 86	Tetrasulfane	●	●	●		●		●			
 Aktisil PF 777	Sillitin Z 86	Alkyl	●	●	●	●	●	●	●			
 Aktisil Q	Sillitin V 90 ¹	Methacrylic			●	●	●	●	●	●	●	
 Aktisil VM 56	Sillitin Z 86	Vinyl	●		●	●		●	●			
 Aktisil VM 56/89	Sillitin Z 89	Vinyl	●		●	●		●	●			
 Aktifit AM	Sifit Z 91	Amino	●	●	●	●	●	●	●	●		●
 Aktifit PF 111	Sifit Z 91	Alkyl	●	●	●	●	●	●	●	●		
 Aktifit PF 115	Sifit Z 91	Amino	●	●	●	●	●	●	●	●		●
 Aktifit Q	Sifit Z 91	Methacrylic	●		●	●	●	●	●	●	●	
 Aktifit VM	Sifit Z 91	Vinyl	●		●	●		●	●	●	●	








● = possible ● = recommendation

¹ internal product quality
Specialties available on request






Technical data sheets and material specifications for the above-mentioned products are available on our website www.hoffmann-mineral.com.

These special fillers are based on Neuburg Siliceous Earth, the surface of which is treated with additives.

The Aktisil and Aktifit products have largely functional groups that enable covalent bonds or intensive interaction with the polymer matrix and produce special effects.

Product name	Application
 Aktisil AM	elastomer-metal composite bearings for vibration isolation, PU elastomers (solid rubbers), roller coverings, seals for pharmaceuticals, sponge rubber, car body seals, window and façade sealing, radiator hoses, cable sheaths, seals and O-rings
 Aktisil MAM-R	like Aktisil Q, but for lesser color neutrality requirements and mechanical properties
 Aktisil PF 216	car body seals, hydraulic and fuel hoses, condenser seals, seals and O-rings, roller coverings, solid tires, full rubber tires, timing belts, bearings for vibration isolation
 Aktisil PF 777	products for which an extremely hydrophobic filler is required to minimize water absorption, e.g. anti-corrosion strips and adhesion primers, sealing tape or sheets, or where a reduction in viscosity must be achieved without processing agents
 Aktisil Q	silicone compounds, silicone turbocharger hoses, seals and molded parts based on HNBR, EPDM and FKM, improvement of oil resistance, condenser seals based on resin-cured butyl rubber
 Aktisil VM 56	window and façade sealing, low-voltage cable sheaths and insulation, radiator hoses, seals, O-rings, sponge rubber, timing belts, roller coverings
 Aktisil VM 56/89	same as VM 56 but for greater color neutrality requirements

The following properties can be significantly improved: tensile strength, tensile modulus, tension and compression set, abrasion resistance, resistance to fluids, electrical resistivity and dielectric loss after exposure to water.

Product name	Application
 Aktifit AM	like Aktisil AM, but with highest color neutrality, avoidance of mold fouling/deposits on dies caused by filler, lower compression set and improved oil resistance with amine crosslinking (AEM, Vamac®, ACM and BIIR), bisphenol crosslinking FKM, thermoplastic EVA and TPU compounds
 Aktifit PF 111	similar to PF 777, but with highest color neutrality, hydrophobic, avoidance of mold fouling/deposits on dies caused by filler, lower compression set, bisphenol crosslinking (FKM)
 Aktifit PF 115	similar to Aktifit AM, but less polar, highly hydrophobic
 Aktifit Q	like Aktisil Q, but with highest color neutrality, hydrophobic, avoidance of mold fouling/deposits on dies caused by filler, improved extrusion properties
 Aktifit VM	like VM 56 and VM 56/89, but with highest color neutrality, hydrophobic, avoidance of mold fouling/deposits on dies caused by filler, lower compression set, high-voltage cable and electrical applications with low dielectric loss, molded parts, peroxide crosslinking FKM


Automotive



Car body seals, solid

Advantages:

- good extrusion properties
- high surface quality
- low moisture content
- high tensile modulus
- low compression set
- high electrical resistance (compared with carbon black)
- avoids deposits on dies caused by filler



EPDM profiles, foamed

Advantages:

- good mixing and dispersion properties
- good extrusion properties
- high surface quality
- high electrical resistance
- cost reduction potential
- avoid deposits on dies caused by filler
- lower water absorption (compared with carbon black)

	Sillitín Z 86	Sillikolloid P 87	Sifit Z 91*	Aktisil PF 216	Aktift PF 115*
Profile quality/extrusion speed	•••	••••	•••	•••	••••
Plating/Mold fouling	••	•••	no	••	no
Tensile strength	•••	••••	•••	••••	••••
Moduli	•••	••••	•••	••••	••••
Compression set	•••	••••	•••	••	••

*less moisture than Sillitín/Sillikolloid/Aktisil

	Sillitín N 75	Sillitín N 85	Sillitín Z 86	Sillikolloid P 87	Sifit Z 91*	Aktisil PF 216	Aktift AM*
Dispersion	•••	••••	••••	••••	••••••	••••	••••••
Profile quality/extrusion speed	••••	•••	••••	••••••	••••••	••••	••••••
Collapse resistance	•••	•••	••••	••••••	••••	••••	••••
Wear	•••	•••	••	•	•••	••	•••
Plating/Mold fouling	•	•	••	•••	no	••	no
Brightness	•	•••	•••	•••	••••••	•••	••••••
Color neutrality	•	•••	•••	•••	••••••	•••	••••••
Matting	•••	•••	••	•	••	••	••
Tensile strength	•••	•••	••••	••••••	••••	••••••	••••••
Tear resistance	•••	•••	••••	••••••	••••	••	••
Moduli	••	••	•••	••••	•••	••••••	••••
Compression set	•••	•••	••••	••••••	•••	•	•
Abrasion resistance	••	••	•••	••••	•••	••••••	••••

*less moisture than Sillitín/Sillikolloid/Aktisil



Direct glazing of fixed side windows

Advantages:

- good mixing and dispersion properties
- long flow time with short vulcanization time
- easy deflashing
- matting
- high surface quality and evenness

	Sillitín Z 86	Sifit Z 91*
Dispersion	••••	••••••
Plating/Mold fouling	•••	no
Compression set	•••	••

*less moisture than Sillitín

Automotive



Molded gaskets, o-rings and radial shaft seals

Advantages:

- very low sieve residue
- good mixing and dispersion properties
- long flow time with short vulcanization time
- easy deflashing
- low compression set
- good resistance against oil, water and acid
- avoidance of mold fouling caused by filler

	Sillitin N 75	Sillitin N 85	Sillitin Z 86	Sillikolloid P 87	Silift Z 91*
Dispersion	•••	••••	••••	••••	•••••
Wear	•••	•••	••	•	•••
Plating/Mold fouling	•	•	••	•••	no
Brightness	•	•••	•••	•••	•••••
Color neutrality	•	•••	•••	•••	•••••
Tensile strength	••	••	•••	••••	•••
Tear resistance	••••	••••	••••	•••••	••••
Compression set	••••	••••	••••	••••	•••

*less moisture than Sillitin/Sillikolloid; very fine cell structure in sponge rubber

low • high ••••• optimum

Specially for diamine crosslinking (ACM, AEM):

Aktifit AM

Tensile strength	•••••
Moduli	••••
Compression set	•
Abrasion resistance	••••
Chemical resistance	••••

Specially for sulphur and metaloxide crosslinking:

Aktisil PF 216

Aktisil AM

Aktifit AM*

	Aktisil PF 216	Aktisil AM	Aktifit AM*
Cure rate	••••	•••••	•••••
Tensile strength	•••••	••••	••••
Moduli	••••	••••	••••
Compression set	•	••	•
Abrasion resistance	•••••	••••	••••
Chemical resistance	•••••	••••	••••

*less moisture than Aktisil

Specially for peroxide crosslinking:

Aktisil VM 56

Aktisil VM 56/89

Aktisil Q¹/²/^{**}

Aktifit VM*

Aktifit Q*

Dispersion	••••	••••	••••	•••••	•••••
Color neutrality	•••	••••	•••••	•••••	•••••
Tensile strength	•••••	•••••	•••••	•••••	•••••
Moduli	•••••	•••••	•••••	•••••	•••••
Compression set	••	••	•	•	•
Abrasion resistance	•••••	••••	••••	•••••	•••••
Chemical resistance	••••	••••	••••	••••	••••

*less moisture

**lower viscosity; best product for silicone rubber

Specially for FKM compounds:

detailed information on page 34

Automotive



Radiator hoses

Advantages:

- high extrusion speed
- high tensile modulus
- low compression set
- coolant resistance
- high electrical resistance

	Sillitin N 85	Sillitin Z 86	Sillitin Z 91*
Dispersion	••••	••••	••••••
Profile quality	•••	••••	••••
Wear	•••	••	•••
Plating/Mold fouling	•	••	no

*less moisture than Sillitin

Specially for sulphur crosslinking:

	Aktisil AM	Aktifit AM*
Cure rate	••••••	••••••
Tensile strength	••••	••••
Moduli	••••	••••
Compression set	••	••
Abrasion resistance	••••	••••
Chemical resistance	••••	••••

*less moisture than Aktisil

Specially for peroxide crosslinking:

	Aktisil VM 56	Aktifit VM*	Aktifit Q*
Tensile strength	••••	••••	••••
Moduli	••••	••••	••••••
Compression set	••	••	•
Abrasion resistance	••••	••••	••••
Chemical resistance	••••	••••	••••

*less moisture than Aktisil



HCR Silicone turbocharger hoses

Advantages:

- high extrusion speed
- high collapse resistance for hose extrusion
- high tensile modulus
- low compression set
- heat resistance
- high oil resistance

	Aktisil Q
Collapse resistance	•••••
Moduli	••••
Compression set	•
Heat resistance	••••••
Oil resistance	••••••



Urea-resistant EPDM gaskets and hoses

Advantages:

- short curing time
- high tensile modulus
- high surface quality
- improved collapse resistance for hose extrusion
- no blooming
- cost reduction potential
- great resistance against urea solution (AdBlue) and hot air aging

	Aktisil VM 56
Collapse resistance	•••••
Moduli	•••••
Heat resistance	•••••
Urea resistance	••••••

Automotive



Air intake hoses EPDM

Advantages:

- quick conversion timer t_{90}
- prevention of mould fouling
- better compression set
- cost reduction potential

	Sillitín N 75	Sillitín Z 86	Silfit Z 91*	Aktisil AM	Aktifit AM*
Cure rate	•••	•••	••••	•••••	•••••
Plating/Mold fouling	•	••	no	••	no
Wear	•••	••	•••	••	•••
Compression set	•••	••••	•••	•••	••

*less moisture than Sillitín/Aktisil

Timing belts

Advantages:


- good processing properties
- good adhesive strength to reinforcing materials
- good dynamic properties
- low compression set
- high oil resistance



	Aktisil PF 216	Aktisil VM 56
Compression set	••	••
Oil resistance	••••	•••••
Sulfur and metaloxide crosslinking	•••••	•••
Peroxide crosslinking	•••	•••••

low • high ••••• optimum

Machine and equipment construction



Conveyor belt skim compounds

Advantages:

- good processing properties
- good calendering properties
- good adhesive strength to reinforcing materials
- high tensile modulus

	Sillitín N 75	Sillitín N 85	Sillitín Z 86
Dispersion	•••	••••	••••
Wear	•••	•••	••
Color neutrality	•	•••	•••

Elastomer-metal composites


Advantages:

- improved elastomer-metal adhesive strength



	Aktisil AM	Aktifit AM*
Dispersion	••••	•••••
Plating/Mold fouling	••	no
Color neutrality	•••	•••••
Compression set	•••	••

*less moisture than Aktisil



Roller coverings and printing blankets

Advantages:

- very low residue > 40 µm
- good mixing and dispersion properties
- good rubber-metal adhesive strength
- excellent grinding properties
- high surface quality
- good for laser engraving
- low dynamic heat build-up
- low compression set
- good resistance against solvents, oil, water, acid

Specially for FKM compounds:
 detailed information on page 34

Sillitin N 85 (puriss)
 Sillitin Z 86 (puriss)
 Silit Z 91*

	Sillitin N 85 (puriss)	Sillitin Z 86 (puriss)	Silit Z 91*
Dispersion	●●●● (●●●●●)	●●●● (●●●●●)	●●●●●
Wear	●●●	●●	●●
Plating/Mold fouling	●	●●	no
Brightness	●●●	●●●	●●●●●
Color neutrality	●●●	●●●	●●●●●

*less moisture than Sillitin

Specially for peroxide crosslinking

Aktisil VM 56
 Aktisil VM 56/89

Aktisil Q**

Aktifit VM*

Aktifit Q*

	Aktisil VM 56	Aktisil VM 56/89	Aktisil Q**	Aktifit VM*	Aktifit Q*
Dispersion	●●●●	●●●●	●●●●	●●●●●	●●●●●
Color neutrality	●●●	●●●●	●●●●	●●●●●	●●●●●
Tensile strength	●●●●	●●●●	●●●●	●●●●	●●●●●
Moduli	●●●●	●●●●	●●●●	●●●●	●●●●●
Compression set	●●	●●	●	●	●
Abrasion resistance	●●●●	●●●●	●●●	●●●●	●●●●●
Chemical resistance	●●●●	●●●●	●●●	●●●	●●●
Dynamic heat build-up	●●	●●	●●	●●	●●

*less moisture

**lower viscosity; best product for silicone rubber

low ● high ●●●●● optimum

Specially for sulphur and metaloxide crosslinking:

Aktisil PF 216

Aktisil AM

Aktifit AM*

	Aktisil PF 216	Aktisil AM	Aktifit AM*
Cure rate	●●●●	●●●●●	●●●●●
Tensile strength	●●●●●	●●●●	●●●●
Moduli	●●●●●	●●●●	●●●●
Compression set	●	●●	●
Abrasion resistance	●●●●	●●●●	●●●●
Chemical resistance	●●●●●	●●●●	●●●●
Dynamic heat build-up	●	●●	●●

*less moisture than Aktisil

Specially for diamine crosslinking (acm, aem):

Aktisil AM

Aktifit AM*

	Aktisil AM	Aktifit AM*
Dispersion	●●●●	●●●●●
Tensile strength	●●●●●	●●●●●
Moduli	●●●●	●●●●
Compression set	●●	●●
Abrasion resistance	●●●●	●●●●
Chemical resistance	●●●●	●●●●
Dynamic heat build-up	●●	●●

*less moisture than Aktisil



Washing machine gaskets and hoses

Advantages:

- long flow time with short vulcanization time
- good balance between tensile strength, tear resistance and compression set
- good suds resistance
- potential substitute for silica
- potential for reducing titanium dioxide and zinc oxide
- avoidance of mold fouling caused by filler
- very low chloride content

Sillitin N 85

Sillitin Z 86

Sillikolloid P 87

Sillitin Z 91*

	Sillitin N 85	Sillitin Z 86	Sillikolloid P 87	Sillitin Z 91*
Dispersion	●●●●	●●●●	●●●●	●●●●●
Wear	●●●	●●	●	●●
Plating/Mold fouling	●	●●	●●	no
Brightness	●●●	●●●	●●●	●●●●●
Color neutrality	●●●	●●●	●●●	●●●●●
Tensile strength	●●●	●●●	●●●●	●●●
Tear resistance	●●●	●●●	●●●●	●●●●
Compression set	●●●	●●●●	●●●●	●●●

*less moisture than Sillitin/Sillikolloid, lowest chloride content

Machine and equipment construction



Hydraulic and fuel hoses, oil-resistant hoses in general

Advantages:

- very good extrusion properties
- high surface quality
- high tensile modulus
- low compression set
- good resistance against fuels, oils, water, acids
- avoids deposits on dies caused by filler

Specially for sulphur and metaloxide crosslinking:

	Aktisil PF 216	Aktisil AM	Aktifit AM*
Cure rate	•••••	•••••	•••••
Dispersion	••••	••••	•••••
Plating/Mold fouling	••	••	no
Tensile strength	•••••	•••••	•••••
Moduli	•••••	•••••	•••••
Compression set	•	••	•
Abrasion resistance	•••••	••••	••••
Chemical resistance	•••••	••••	••••

*less moisture than Aktisil

Sillitin Z 86
Sifit Z 91*

Dispersion	••••	•••••
Plating/Mold fouling	••	no
Brightness	••••	•••••
Color neutrality	••••	•••••
Compression set	••••	••

*less moisture than Sillitin

Specially for diamine crosslinking (ACM, AEM):

	Aktisil AM	Aktifit AM*
Dispersion	••••	•••••
Tensile strength	•••••	•••••
Moduli	••••	••••
Compression set	••	••
Abrasion resistance	••••	••••
Chemical resistance	••••	••••

*less moisture than Aktisil

Specially for peroxide crosslinking:

	Aktisil VM 56	Aktisil VM 56/89	Aktisil Q**	Aktifit VM*	Aktifit Q*
Dispersion	••••	••••	••••	•••••	•••••
Plating/Mold fouling	••	••	•	no	no
Color neutrality	••••	••••	•••••	•••••	•••••
Tensile strength	•••••	•••••	•••••	•••••	•••••
Moduli	••••	••••	••••	•••••	•••••
Compression set	•••	•••	••	••	•
Abrasion resistance	••••	••••	••••	••••	••••
Chemical resistance	••••	••••	•••••	••••	••••

*less moisture

**lower viscosity; best product for silicone rubber

Specially for FKM compounds:
detailed information on page 34

low • high ••••• optimum



Diaphragms for expansion vessels

Advantages:

- low viscosity
- high tear resistance
- high elongation at break

	Sillitin Z 86
Viscosity	••
Tear resistance	••••
Elongation at break	••••

Cable and electrical industry



Cable sheaths, cable insulation

Advantages:

- very good extrusion properties
- medium to high tensile strength
- good compressive properties at high temperature
- good hot set properties
- high electrical resistivity, also after immersion in water
- very low dielectric loss, also after immersion in water, even without additional silane in the compound
- avoidance of deposits on dies caused by filler
- good resistance against oil, water, acids

	Sillitín Z 86	Silift Z 9T*
Dispersion	••••	••••••
Plating/Mold fouling	••	no
Brightness	••••	••••••
Color neutrality	••••	••••••
Compression set	••••	••
Dielectric loss	••••	••

*less moisture than Sillitín

Specially for sulphur and metaloxide crosslinking:

	Aktisil PF 216	Aktisil AM	Aktifit AM*
Dispersion	••••	••••	••••••
Plating/Mold fouling	••	••	no
Cure rate	••••	••••••	••••••
Tensile strength	••••••	••••••	••••••
Moduli	••••••	••••••	••••••
Compression set	•	••	•
Abrasion resistance	••••••	••••	••••
Chemical resistance	••••••	••••	••••

*less moisture than Aktisil

Specially for peroxide crosslinking

	Aktisil VM 56	Aktisil VM 56/69	Aktisil Q*/**	Aktifit VM*
Dispersion	••••	••••	••••	••••••
Plating/Mold fouling	••	••	•	no
Color neutrality	••••	••••	••••••	••••••
Tensile strength	••••••	••••••	••••	••••••
Moduli	••••••	••••	••••	••••••
Compression set	••••	••••	••	••
Abrasion resistance	••••	••••	••••	••••
Chemical resistance	••••	••••	••••	••••
Electrical resistivity after exposure to water	••••••	••••••	••••••	••••••
Dielectric loss	••	••	••	•***

*less moisture than Aktisil

**lower viscosity; best product for silicone rubber

***even after storage in water; even without additional silane

Cable and electrical industry




Medium- and high voltage cable insulations

Advantages:

- very low sieve residues in ppm range
- excellent dispersion properties
- very good extrusion properties
- high tensile strength
- very high electrical resistivity, even after storage in water
- very low dielectric loss, even after storage in water, even without additional silane
- avoids mold fouling/deposits on dies caused by filler
- good resistance to oils, water and acids

	Sifit Z 91	Aktifit VM
Moisture	••	•
Increase in humid climatic conditions	low	no
Dispersion	•••••	•••••
Residue	•	•
Tensile strength	••••	••••
Electrical resistivity after exposure to water	•••	•••••
Dielectric loss after exposure to water	••	•



High voltage isolators

Advantages:

- very low sieve residues in ppm range
- excellent dispersion properties
- high elongation at break
- high tear resistance
- very high electrical resistivity
- high tracking resistance

	Aktist Q	Aktifit VM
Cure rate	••••	••••
Tensile strength	••••	••••
Elongation at break	••••	••••
Tear resistance	••••	••••
Electrical resistivity	••••	••••
Tracking resistance	••••	••••

Capacitor gaskets

Advantages:

- very low sieve residue
- very low chloride content
- long flow time with short vulcanization time
- high tensile modulus
- low compression set
- good hot air aging properties
- sealing tightness at high soldering temperatures



Specially for peroxide cross-linked EPDM compounds:

	Aktisil VM 56	Aktifit VM*
Processing properties	●●●●	●●●●●
Plating/Mold fouling	●●	no
Moduli	●●●●	●●●●●
Compression set	●●●	●●
Ageing properties	●●●	●●●●

*less moisture than Aktisil

Specially for resin crosslinking of butyl rubber (IIR):

	Aktisil VM 56	Aktisil MAM-R	Aktifit VM**
Processing properties	●●●●	●●●●	●●●●●
Moduli	●●●●	●●●●●	●●●●●
Compression set	●●	●	●
Ageing properties	●●●	●●●●	●●●●
Electrical resistivity	●●●●●	●●●●●	●●●●●


*less moisture than Aktisil

**counterpart to surface-treated calcined kaolin with improved processing, better ageing properties and lower compression set

Floor coverings

Advantages:

- good mixing and dispersion properties
- good calendaring properties
- long flow time, short vulcanization time
- low residual indentation
- less white scratch marks
- high surface quality
- high abrasion resistance
- good resistance to aggressive substances



	Sillitn N 87*	Sillitn Z 86**	Sillitn Z 89**
Brightness	●●●	●●●	●●●●
Color neutrality	●●●	●●●	●●●●
Abrasion resistance	●●●	●●●●	●●●●

*standard product

**preferably with replacement of silica and existing filler in combination with silane



Roofing membranes

Advantages:

- good calendaring properties
- high tensile modulus
- good resistance to aggressive substances such as acids and other chemicals

	Sillitn N 75	Sillitn N 85	Sillitn Z 86	Sillitn Z 89
Dispersion	●●●	●●●●	●●●●	●●●●
Brightness	●	●●●	●●●	●●●●
Color neutrality	●	●●●	●●●	●●●●
Wear	●●●	●●●	●●	●●
Compression set	●●●	●●●	●●●●	●●●●



Anti-corrosion lining

Advantages:

- good processing properties
- good calendaring properties
- good resistance to aggressive substances such as acids and other chemicals

	Sillitín N 75	Sillitín N 85	Sillitín Z 86	Aktisil PF 777***	Aktifit PF 111**
Dispersion	•••	••••	••••	••••	•••••
Brightness	•	•••	•••	•••	•••••
Color neutrality	•	•••	•••	•••	•••••
Wear	•••	•••	••	••	•••
Compression set	•••	•••	••••	••	••
Water swelling of non-crosslinked corrosion protection tapes	•••	•••	•••	•	•
Adhesion to steel	•••	•••	•••	••••	••••
Hydrophobicity	no	no	no	yes	yes

*less moisture than Sillitín

**filler for non-crosslinked butyl corrosion protection tapes with minimized water swelling, hydrophobic filler for adhesion primers with improved adhesion to steel



Building profiles (window and façade sealing)

Advantages:

- low to very low moisture content
- enables high loading of filler and plasticizer
- excellent extrusion properties
- high surface quality
- high tensile modulus
- low compression set


	Sillitín Z 86	Sillikolloid P 87	Aktisil VM 56***	Sillitín Z 89	Aktisil VM 56/89***	Silfit Z 91*	Aktifit VM**/**
Dispersion	••••	••••	••••	••••	••••	•••••	•••••
Profile quality/extrusion speed	•••	•••	••••	••••	•••••	•••••	•••••
Collapse resistance	••••	••••	••••	••••	••••	••	••
Plating/Mold fouling	••	•••	••	••	••	no	no
Potential for increase loading of filler and plasticizer	•••	•••	••••	•••	••••	•••	••••
Brightness	•••	•••	•••	••••	••••	•••••	•••••
Color neutrality	•••	•••	•••	••••	••••	•••••	•••••
Tensile strength	•••	••••	•••••	•••	•••••	•••	•••••
Tear resistance	•••••	•••••	•••	•••••	•••	••••	•••
Moduli	•••	••••	•••••	•••	•••••	••••	•••••
Compression set	•••	••••	••	•••	••	••	•

*less moisture than Sillitín/Sillikolloid, very fine cell structure in sponge rubber

**less moisture than Silfit

***lower peroxide dosage possible

Construction industry




Solar panel tubes for swimming pools

Advantages:

- high extrusion speed with good contour shaping and smooth surfaces
- low compression set
- high tensile strength
- high filler concentration for high thermal conductivity

	Aktisil VM 56	Aktifit VM*
Extrusion properties	••••	••••••
Plating/Mold fouling	••	no
Brightness	••••	••••••
Color neutrality	••••	••••••
Tensile strength	••••	••••
Compression set	••	•
Hydrophobicity	no	yes

*less moisture than Aktisil



Sealing profiles for road and tunnel construction

Advantages:


- very good extrusion properties
- low moisture content
- low compression set

	Sillitín N 75	Sillitín N 85	Sillitín Z 86
Dispersion	•••	••••	••••
Brightness	•	•••	•••
Color neutrality	•	•••	•••
Wear	•••	•••	••
Compression set	•••	••	••••

Sealing tape

Advantages:

- good processing properties
- good calendering properties
- balanced ratio of tensile stress/ modulus/tear resistance



	Sillitín N 75	Aktisil PF 777*	Aktifit PF 111*
Brightness	•	••••	••••••
Color neutrality	•	••••	••••••
Water absorption (also in unvulcanized state)	•••	•	•
Moduli	••	•	••
Hydrophobicity	no	yes	yes

*less moisture than Sillitín

Other applications



FKM Compounds

Advantages:

- very low sieve residue
- good mixing and dispersion properties
- high tensile strength
- high abrasion resistance
- long flow time with short vulcanization time
- good resistance to substances (fuel, oil, water, acid)
- low compression set
- easy deflashing
- avoidance of mold fouling on dies caused by filler

Bisphenol crosslinking:

	Sifit Z 91	Aktifit AM	Aktifit PF 115	Aktifit PF 111	Aktisil Q
Viscosity	•••	•••	••	••	••
Cure rate	•••	•••••	•••••	•••••	•••
Tensile strength	•••	••••	••••	••••	•••
Elongation at break	•••••	•••	••••	••••	••••
Compression set	••*	•••	•••	••*	••
Compression set, acc. to VW	••••*	•••	•••	••*	••
Abrasion resistance	•••	••••*	••••*	•••	••
Water resistance	•••	••••	••••*	•••	••••
Fuel resistance	•••	••••	••••	••••*	•••
Oil resistance	•••	•••	••••*	••••	•••

*depending on polymer and filler loading

Peroxide crosslinking:

	Sifit Z 91	Aktifit VM	Aktifit PF 111	Aktifit AM	Aktifit PF 115	Aktisil AM	Aktisil Q
Viscosity	••••	••••	••••	•••	•••	•••	••
Cure rate	•••••	•••	•••	•••••	•••••	•••••	•••
Tensile strength	•••	•••••	••••	••••	•••	•••••	•••
Elongation at break	•••••	••	•••••	••••	•••••	••••	••
Moduli	••••	••••	•••	•••••	••••	•••••	••••
Tear resistance	•••••	••	•••	•••	•••••	•••	•••
Compression set	••	••	••**	•••	•••	•••	•*
Compression set, acc. to VW	••	••	••	••	•••	•	••
Abrasion resistance	••	••••	•••	•••	•••	•••	•••
Heat resistance	••	•••••**	•••	•••••	••	•••••	•••••
Resistance to acetic acid	••	•••••****	•••••***	••••	•••••****	•••	•••••
Fuel resistance	•••	•••	•••	•••	•••	•••	•••
Oil resistance	••••	•••	••••	•••••	•••	•••••	•••••

*no post-cure

**at high temperatures

***lowest weight increase

****lowest hardness change

*****positive change of tensile strength and elongation at break

Other applications



Silicone rubber compounds

Advantages:

- good extrusion properties and collapse resistance
- reduced stickiness
- no blooming
- drier surface
- very good oil resistance
- low tension and compression set without post cure
- partial replacement of ATH with Aktisil Q, Aktifit Q or Silfit Z 91 provides the same flame-retardant properties of pure ATH

Peroxide crosslinked silicone rubber compounds:

	Silfit Z 91	Aktifit Q	Aktisil Q*
Suitable for all peroxidea	no**	yes***	yes
Compression set	••••	•••***	•
Brightness	•••••	•••••	••••
Color neutrality	•••••	•••••	••••

For flame retardant compounds, partial replacement of ATH up to 30%

	Silfit Z 91	Aktifit Q	Aktisil Q*
Retained flame retardancy	yes	yes	yes
Mechanical properties	•••	•••	•••••

*even in high loadings up to 100 phr, even for chlorine-free peroxide

**with DBPH (2,5-Bis-[tert-butyl-peroxy]-2,5 dimethylhexane): up to 25 phr; with DCBP (Di-[2,4-dichlorobenzoyl]peroxide): up to 75 phr; with dicumyl peroxide: no

***with DBPH: up to 50 phr; increase of tear resistance without changing compression set up to 25 phr with DCBP: up to 75 phr with dicumyl peroxide: up to 50 phr, improvement of tear resistance at high concentration

****up to 25 phr

Silicone rubber compounds, addition crosslinked (Pt-catalyzed) up to 25 phr

	Silfit Z 91	Aktifit VM	Aktifit Q	Aktisil Q
Tear resistance (Graves)	••••	••	••••	••
Moduli	••••	••	••••	••••
Compression set	••	••	••	•
Heat resistance	••	••	••	••••
Oil resistance	••••	••••	••••	•••••
Brightness	•••••	•••••	•••••	••••
Color neutrality	•••••	•••••	•••••	••••

Poatable water seals peroxide cross-linked

Advantages:

- cost reduction potential
- low mooney viscosity
- short vulcanisation time
- UBA positive list part 1 compliant, meets BfR purity requirements
- potential to reduce the PAH concentration in the compound by partial replacement of the carbon black



	Sillitun Z 86	Aktisil VM 56
Viscosity	•••	•••
Vulcanization time	•••	•••
Carbon black exchange potential	••	••••
Cost reduction potential	••••	••

Other applications



Pharmaceutical closures

Advantages:

- high purity
- good mixing and dispersion properties
- easy deflashing
- low compression set
- low fragment release and good self-sealing after needle penetration

	Sillitín N 85*/ Sillitín Z 86*	Sifit Z 91	Aktifit AM**	Aktifit VM***
Moisture	•••	••	••	•
Dispersion	••••	•••••	•••••	•••••
Brightness	•••	•••••	•••••	•••••
Color neutrality	•••	•••••	•••••	•••••
Plating/Mold fouling	••	no	no	no
Compression set	•••	••	•	•

*standard product

**especially for diamine crosslinking

***especially for crosslinking with peroxides, even without coagents good curing properties



(No specific product recommendation)

Food contact materials

Here you will find further information on safety regulations and the applicable regulations.



Shoe components

Advantages:

- good processing properties
- long flow time with short vulcanization time
- easy deflashing

	Aktifit AM	Aktifit VM
Brightness	•••••	•••••
Color neutrality	•••••	•••••
Pigment reduction	••••	••••
Sulfur crosslinking	•••••	••
Peroxide crosslinking	••	•••••

Solid tires and spinning cot

Advantages:

- good processing properties
- long flow time with short vulcanization time
- easy deflashing
- low rolling resistance
- low compression set



	Sillitín Z 86	Aktisil PF 216
Dispersion	••••	••••
Compression set	•••	••
Rolling resistance	•••	••
Abrasion resistance	••	••••

Basic properties of (Calcined)
 Neuburg Siliceous Earth

Advantages for users

- | | |
|--|---|
| low moisture, low moisture absorption | > less effort for pre-drying, pre-drying may not be necessary, less polymer degradation with hydrophobic products |
| high fineness, very low sieve residue, excellent dispersion properties | > high surface quality, no spots or agglomerates, even matting |
| hard silicate mineral | > very good acid resistance, abrasion resistance, scratch resistance |
| polymer-specific adaptation via functionalization | > low compression set, very good abrasion and scratch resistance |
| low CO ₂ -footprint | > reduction of product carbon footprint of TPE |

Windshield water guide trim, SEBS compound on PP core in injection molding process

Advantages:

- sufficient melt flowability
- no flow lines
- evenly matte surface without "tiger stripes"



	Sillitín Z 86 puriss	Aktisil AM	Aktifit AM
Even matting	•••••	•••••	•••••
Dispersion	•••••	•••	•••••
Scratch resistance	•••	•••••	•••••

TPE

Pickup truck liners, SEBS-PE compound

Advantages:


- reduction of joint line visibility
- high ultimate elongation
- very good scratch resistance
- reduced shrinkage/warpage
- high tensile strength
- improvement of rigidity
- very good dispersion properties
- very good surface quality



Aktifit AM

Reduction of joint line visibility	●●●●●
Rigidity	●●●●●
Surface quality	●●●●●
Scratch resistance	●●●●●

Packaging seals like screw cap seals for acidic contents on a SEBS basis



Advantages:

- very good dispersion properties
- good extrusion properties
- very good acid resistance
- hydrophobic properties
- good mechanical properties
- low compression set
- high purity, suitable for food contact materials

Aktifit VM

Hydrophobicity	●●●●●
Acid resistance	●●●●●
Compression set	●

niedrig ● hoch ●●●●● optimum













Basic properties of Calcined Neuburg Siliceous Earth

Advantages for users


low moisture, low moisture absorption	> less effort for pre-drying, pre-drying may not be necessary, less polymer degradation with hydrophobic products
high fineness, very low sieve residue, excellent dispersion properties, morphology	> high surface quality, no spots or agglomerates, supports pigment dispersion (spacer effect), potential pigment savings
high brightness and color neutrality	> enables white products without a yellow tint, low requirement for white pigments such as titanium dioxide
largely isotropic properties	> low warpage, medium increase in stiffness
hard silicate mineral	> very good acid resistance, abrasion resistance, scratch resistance
polymer-specific adaptation via functionalization	> very good scratch resistance, high impact strength, high ultimate elongation
temperature resistance	> can also be used for technical thermoplastics, no by-products or decomposition
low CO ₂ -footprint	> reduction of product carbon footprint of thermoplastic molded parts

Selection criteria for thermoplastic molded parts

Aktifit

Polymer/Application	Recommended product	Alternative product recommendation	Remarks	flowability	ultimate elongation	impact strength	scratch resistance	tensile strength	flexural strength	no crosslinking
PA (polyamide)	 Aktifit AM			●	●	●	●			
PPA (polyphthalamide)	 Aktifit AM	Aktifit PF 115		●	●	●	●			
PBT (polybutylene terephthalate)	 Aktifit VM	Aktifit Q			●	●	●			
PC (polycarbonate)	 Aktifit VM	Aktifit PF 111 Aktifit Q	Aktifit VM and Aktifit PF 111 also for higher filler levels without any significant polymer degradation		●	●	●			
PP (polypropylene)	 Aktifit AM  Aktifit AM + MAH-modified polymer	Silfit Z 91 + MAH-modified polymer Aktifit PF 111	Aktifit PF 111 primarily for homopolymers for high ultimate elongation and impact strength with good flowability		●	●	●			
PK (aliphatic polyketone)	 Aktifit AM	Aktifit PF 115		●	●	●	●		●	●
PPS (polyphenylene sulfide)	 Aktifit PF 115	Aktifit AM		●		●		●	●	
other polymers	 Aktifit AM  Aktifit VM  Aktifit PF 111  Aktifit PF 115  Aktifit Q		depending on the polymer for optimal interaction and other requirements	●	●	●	●	●	●	

Thermoplastic molded parts



Aktifit AM

Melt flowability	●●●●
Shrinkage/warpage	●●
Weld line strength	●●●●
Scratch resistance	●●●●
Ultimate elongation/flexibility	●●●●●
Impact strength	●●●●●*

*even at low temperatures

Housings and impact resistant molded parts, PA 6 and PA 66

Advantages:

- high melt flowability
- low warpage
- extremely high ultimate elongation
- extraordinarily high impact strength, even at low temperatures
- great weld line strength
- no graying of black compounds
- enables low warpage, impact-resistant parts without or with little impact modifier as alternative to PA 6 GF15 impact modified



Scratch-resistant PP co-polymer compounds for automotive interior trim


Advantages:

- very good scratch resistance
- high ultimate elongation
- high impact strength, even at low temperatures

Polyphenylene sulfide (PPS)

Advantages:

- bright and neutral color of the compound
- high impact strength
- high strength
- high melt flowability
- low warpage



Aktifit AM
Aktifit PF 115

Brightness	●●●	●●●●
Color neutrality	●●●	●●●●
Increased stiffness	●●●	●●●●
Flexural strength	●●●	●●●●

Silift Z 91
Aktifit AM

Scratch resistance	●●	●●●●
Ultimate elongation	●●●●	●●
Impact strength	●●●●*	●●●●*
Notched impact strength	●●	●●*

when MAH-modified polymer is added:

Scratch resistance	●●●	●●●●
Ultimate elongation	●●●	●●●
Impact strength	●●●	●●●●*
Notched impact strength	●●	●●●●*


*even at low temperatures

Thermoplastic molded parts


3D printing, filament printing of ABS, FFF process

Advantages:

- easy handling during compound- ing (low dust, easily dispersible)
- reduced warpage of the component
- very good mechanical properties
- comparable layer adhesion as unfilled ABS
- faster print speed
- lower printing temperature enables processing even on printer without heated build chamber/ print bed



	Sifit Z 91	Aktifit AM	Aktifit PF 115
Shrinkage/warpage	•	••	••
Layer adhesion	••••	••••	•••••
Impact strength	•••	••••	••
Mechanical properties	•••	•••	•••
Cost-effective	••••	•••	•••



	Aktifit VM
Melt flowability	••••
Shrinkage/warpage	••
Heat deflection temperature HDT	••••
Increased stiffness, tensile strength and flexural strength	•••••
Ultimate elongation/flexibility	•••••
Impact strength	•••••*

*even at low temperatures

Polybutylene terephthalate (PBT)

Advantages:

- good melt flowability
- bright and neutral color of the compound
- extremely high ultimate elongation
- high stiffness, tensile strength and flexural strength
- increase of HDT
- extraordinarily high impact strength, even at low temperature
- retention of good mechanics even with black coloring
- low warpage



Transport packaging for wafer canister, HDPE

Advantages:

- improved physical properties
- very smooth surface

	Aktifit AM
Surface quality	•••••
Improvement of physical properties	•••••

Polycarbonate (PC)

Advantages:

- low warpage
- high translucency
- high thermal stability of the melt (low polymer degradation), even at higher VM level
- good scratch resistance
- high ultimate elongation
- extraordinarily high impact strength, even at higher VM level




	Aktifit VM	Aktifit PF 111	Aktifit O*
Thermal stability of the melt	••••	••••	
Impact strength	•••••	••••	preferably for PC blends, e.g. PC/ASA
Scratch resistance	••••	••••	
Translucency	••••	••••	

Thermoplastic molded parts

Wood-plastic composites (WPC), handles, extruded profiles


Advantages:

- high throughput/extrusion speed
- smooth and optically even surfaces
- improved scratch resistance
- improved physical properties (impact strength, tensile strength)



Aktifit AM

Scratch resistance	●●●●
Surface quality	●●●●
Improvement of mechanical properties	●●●●



Aktifit AM

Aktifit PF 115

Melt flowability, no crosslinking	●●●●	●●●●
Increased stiffness, tensile strength and flexural strength with good stretching properties	●●●●	●●●●
Impact strength and notched impact strength	●●●●*	●●●●*
Brightness	●●●	●●●●
Color neutrality	●●●	●●●●

*even at low temperatures

Polyketon (PK)

Advantages:











- good flowability and melt stability, no crosslinking
- increased stiffness, tensile strength and flexural strength with good stretching properties
- bright and neutral color of the compound
- high impact strength, even at low temperature
- low warpage

low ● high ●●●●● optimum

Basic properties of (Calcined) Neuburg Siliceous Earth

Advantages for users

low moisture, low moisture absorption	> less effort for pre-drying, pre-drying may not be necessary, less polymer degradation with hydrophobic products
high fineness, very low sieve residue, excellent dispersion properties, refractive index similar to polymers	> good transparency, high light transmission in the visible range, very thin film thicknesses possible
chemical/mineralogical composition	> infrared barrier
high brightness and color neutrality, morphology	> supports pigment dispersion (spacer effect), potential pigment savings
morphology and choice of different particle sizes	> low coefficient of friction/anti-blocking, high gloss or matting, low haze or higher haze, improvement of film processing/manufacturing properties by increasing modulus
relatively low specific area	> almost no adsorption of additives
polymer-specific adaptation via functionalization	> higher impact strength, scratch resistance, printability
low CO ₂ -footprint	> reduction of product carbon footprint of thermoplastic films

Polymer/application	Recommended product	Alternative product recommendation	Antiblock additive	Cost reduction	Film workability/finishing	Mechanical properties with-out increase of melting point	Matting	IR-Absorption
BO PET (biaxially-oriented polyethylene terephthalate)	 Aktifit VM	Silfit Z 91 Aktifit Q	•	•				
PE, LDPE	 Silfit Z 91  Sillitin V 88  Aktifit PF 111  Sillitin Z 89 puriss	Aktifit AM	•	•				
PE/EVA copolymers	 Silfit Z 91  Sillitin V 88	Aktifit AM	•	•	•	•		
TPU	 Aktifit AM	Sillitin V 88 Aktifit PF 115	•				•	
Greenhous films with IR barrier based on LDPE and PE/EVA	 Sillitin V 88  Sillitin Z 89 puriss  Silfit Z 91	Aktisil Q Aktifit PF 111 Aktifit PF 115 Aktifit VM Aktifit Q Aktifit AM	•					•

Thermoplastic films

Films with anti-blocking, packaging and technical films

Advantages:

- low coefficient of friction
- good transparency
- high gloss
- low haze



PET, biaxially stretched, film thickness 15 to 50 µm:

	Sifit Z 91	Aktifit VM
Moisture	••	•
Increase in humid climatic conditions	low	no
Coefficient of friction	•	•
Optical properties, transparency, gloss, low haze	•••••	•••••

LLDPE and LPDE blown films concentration 0.3–1%:

	Silitin V 88*	Silitin Z 89 puriss**	Sifit Z 91**	Aktifit PF 111**
Anti-blocking (coefficient of friction)	••••	••••	••••	••••
Color neutrality	•••	••	•••••	•••••
Gloss	•••	••••	••••	••••
Clarity	•••	••••	••••	••••
Light scattering (Haze)	•••	••	••	••
Moisture	•••	•••	••	•
Increase in humid climatic conditions	•	••	low	no
Hydrophobicity	no	no	no	yes
Interaction with slip additives	••	•••	••	•

*especially for films with higher thickness

**preferably for films up to 30 µm

Low melting point films with high EVA content

Advantages:

- low coefficient of friction
- good transparency
- improvement of film processing/ manufacturing properties by increasing modulus without increasing the melting temperature
- very good anti-blocking properties, easy opening of film tube
- reduced wastage, increased productivity



concentration 10–15%:

	Sifit Z 91	Silitin V 88*	Aktifit AM
Antiblocking	•••	••••	•••
Mechanical properties	•••	•••	••••


*especially for films with higher thickness

Thermoplastic films

Matting of TPU-films

Advantages:

- good matting
- good scratch resistance
- anti-blocking



	Sillitn V 88*	Aktifit AM**	Aktifit PF 115**
Matting	●●●●	●●	●●
Antiblocking	●●●●	●●	●●
Dispersion	●●●	●●●●	●●●●
Interaction with TPU matrix	●	●●●●	●●●●
Scratch resistance	●●●	●●●●	●●●●
Hydrophobicity	no	no	yes

*especially for films with higher thickness

**for thin and very thin films

Greenhouse film with IR barrier

Advantages:

- very low residue
- good dispersion properties
- good anti-blocking properties
- high light transmission in the photosynthetically active range (400 to 700 nm)
- light-scattering properties adjustable per product type
- high infrared barrier, particularly in the terrestrial radiation range (7 to 13 μm)



	Silfit Z 91	Sillitn Z 89 puriss	Sillitn V 88
IR barrier	●●●●	●●●●	●●●●●
Transmission in PAR	●●●●●	●●●●	●●●
Light scattering	●●●	●●	●●●●●
Light scattering (Haze)	●●	●●	●●●
Gloss	●●	●●●●	●●
Color neutrality	●●●●	●●	●●●