





Neuburg Siliceous Earth in toughened 2K-epoxy-structural-adhesive

Author: Petra Zehnder




- Introduction
- System 1: Component A with epoxy-silicone block copolymer
 - Experimental
 - Results
 - Summary
- System 2: Component B with reactive liquid rubber (ATBN)
 - Experimental
 - Results
 - Summary
- Appendix



Status Quo

- Adhesive bonding is already replacing conventional mechanical joining techniques in many technical applications.
- Structural adhesives are becoming increasingly important, particularly in vehicle and construction engineering.
- 1- or 2-component epoxy-resin based adhesives offer high strength and good chemical and temperature resistance.
- Toughness modifiers are often added to improve flexibility and thus increase shear and peel strength.
- Suitable fillers can also help to optimize the formulation.



System 1

Component A with epoxy-silicone block-copolymer

System 2

Component B with reactive liquid rubber (ATBN)




Formulation

Component A		Parts by weight [pbw]		
Epikote Resin 828LVEL	Epoxy-resin based on bisphenol A	80	80	80
Albiflex 297	Epoxy-silicone block-copolymer	20	20	20
Dynasylan 9116	Alkyl silane, adhesion promoter	3	3	3
Fumed silica	Filler	---	5	---
Neuburg Siliceous Earth	Filler	---	---	50
Total		103	108	153
Component B				
Ancamine 2719	Aliphatic amine (mannich base)	34.37	34.37	34.37
Total A + B		137.37	142.37	187.37

Preparation





Filler characteristics

	Particle size		Color CIELab			Oil absorption [g/100g]	Density [g/cm ³]	Specific surface area BET [m ² /g]	Surface treatment
	d ₅₀ [μm]	d ₉₇ [μm]	L* [-]	a* [-]	b* [-]				
Fumed silica	-	-	-	-	-	-	2.0	80-120	ja
Sillitin V 85	4.5	18	93.3	1.0	9.2	45	2.6	10	-
Sillitin Z 86 puriss	1.9	9	93.9	1.0	9.7	55	2.6	12	-
Aktisil PF 777	2.2	10	93.6	1.2	10.0	35	2.6	9	alkyl functionalized
Aktisil Q	4.0	18	94.7	0.3	4.1	43	2.6	6	methacryl functionalized


Structure of Neuburg Siliceous Earth





Viscosity Component A

MCR 300, platte/platte PP25, measuring 7d after preparation



The addition of the filler increases the viscosity noticeably, especially in the low shear range.

Despite the dosage of 50 pbw, **Aktisil Q** remains at a very low level, whereas **Aktisil PF 777** gives the highest viscosity.




Storage stability

Sedimentation	storage at room temperature for up to 8 weeks: no sediment	✓
Rheology	storage at room temperature for up to 12 weeks: no change in rheology	✓



Viscosity Component A+B

MCR 300, plate/plate PP25



After adding the low-viscosity hardener:


Aktisil Q still shows the lowest viscosity, whereas the other fillers tested result in an ascending ranking of low shear viscosity or yield point.

Aktisil PF 777 marks the highest value after silica and thus the most pronounced shear thinning and thixotropy.



Lap Shear Strength

DIN EN 1465, Cr3 passivated aluminum, adhesive layer thickness 100 µm




Neuburg Siliceous Earth results in a similar to slightly increased lap shear strength compared to the unfilled formulation or the competitor silica.




T-Peel Test

DIN EN ISO 11339, Cr3 passivated aluminum, adhesive layer thickness 100 µm



With
Neuburg Siliceous Earth,
the peel resistance can be
more than tripled.



Rating


	Fumed silica	Sillitin V85	Sillitin Z 86 puriss	Aktisil PF 777	Aktisil Q
Viscosity	↑↑	↑↑	↑↑	↑↑	0/↑
Lap shear strength	0	0 / +	0	0 / +	0
Peel resistance	0	++	++	++	++
Cost aspect	---	+++	+++	++	++
Note		standard product	easy to disperse	rheologically active	low viscosity

Benefits of
Neuburg Siliceous Earth
 vs. unfilled formulation:

comparable or higher
 lap shear strength

significantly higher
 peel resistance

positive cost aspect
 through the use of filler




System 1

Component A with epoxy-silicone block-copolymer


System 2

Component B with reactive liquid rubber (ATBN)



Formulation

Component A		Parts by weight [pbw]	
Epikote Resin 320	Epoxy-resin based on bisphenol A/F	100	100
Neuburg Siliceous Earth	Filler	---	50
Total		100	150
Component B			
Epikure Curing Agent 05903	Hardener (mannich base)	34	34
Hypro 1300x16 ATBN	reactive liquid rubber	8.5	8.5
Total A + B		142.5	192.5

Preparation 



Filler characteristics

	Particle size		Color CIELab			Oil absorption [g/100g]	Density [g/cm ³]	Specific surface area BET [m ² /g]	Surface treatment
	d ₅₀ [μm]	d ₉₇ [μm]	L* [-]	a* [-]	b* [-]				
Sillitin V 85	4.5	18	93.3	1.0	9.2	45	2,6	10	-
Sillitin Z 86 puriss	1.9	9	93.9	1.0	9.7	55	2,6	12	-
Aktisil PF 777	2.2	10	93.6	1.2	10.0	35	2,6	9	alkyl functionalized


Structure of Neuburg Siliceous Earth






Viscosity Component A

MCR 300, platte/platte PP25, measuring 7d after preparation





The addition of the filler increases the viscosity noticeably, especially in the low shear range.

Sillitin V 85 remains at a moderate level despite the dosage of 50 GT, whereas **Aktisil PF 777** gives the highest viscosity




Storage stability

Sedimentation	storage at room temperature for up to 8 weeks: no sediment	
Rheology	storage at room temperature for up to 12 weeks: no change in rheology	



Viscosity Component A+B

MCR 300, plate/plate PP25



After adding the hardener:


Sillitin V 85 still shows the lowest viscosity, whereas the other fillers tested result in an ascending ranking of low shear viscosity or yield point.

Aktisil PF 777 marks the highest value and thus the most pronounced shear thinning and thixotropy.




Lap Shear Strength

DIN EN 1465, Cr3 passivated aluminum, adhesive layer thickness 100 μm




Neuburg Siliceous Earth results in a noticeable increased lap shear strength.



T-Peel Test

DIN EN ISO 11339, Cr3 passivated aluminum, adhesive layer thickness 100 µm



The peel resistance with **Neuburg Siliceous Earth** is approximately at the level of the unfilled formulation.



Rating

	Sillitin V85	Sillitin Z 86 puriss	Aktisil PF 777
Viscosity	↑↑	↑↑	↑↑
Lap shear strength	+	0 / +	+
Peel resistance T-Peel	0	0 / -	0 / -
Cost aspect	+++	+++	++
Note	standard product	easy to disperse	rheologically active

Benefits of
Neuburg Siliceous Earth
 vs. unfilled formulation:

comparable or higher
 lap shear strength

comparable peel resistance

positive cost aspect
 through the use of filler



We supply materials for good ideas!


HOFFMANN MINERAL GmbH
Muenchener Straße 75
DE-86633 Neuburg (Donau)

Phone: +49 8431 53-0
Internet: www.hoffmann-mineral.com
E-mail: info@hoffmann-mineral.com

Our applications engineering advice and the information contained in this memorandum are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.



Neuburg Siliceous Earth




A natural combination of corpuscular Neuburg silica and lamellar kaolinite: a loose mixture impossible to separate by physical methods. The silica portion exhibits a round grain shape and consists of aggregated primary particles of about 200 nm diameter.





Morphology of Neuburg Siliceous Earth





Preparation System 1

<p>Component A</p>	<p>Speedmixer</p> <p>Resin, Abiflex and silane + first part of filler 60 s @ 1000 rpm + 120 s @ 2000 rpm</p> <p>+ rest of filler 30 s @ 800 rpm</p> <p>Clean lid and rim 30 s @ 800 rpm</p> <p>Clean lid, rim and bottom 60 s @ 1000 rpm</p> <p>Clean lid, rim and bottom 300 s @ 2000 rpm</p> <p>Clean lid, rim and bottom 60 s @ 1000 rpm + 120 s @ 2000 rpm</p>
<p>Mixing Component A+B</p>	<p>Speedmixer</p> <p>60 s @ 1000 rpm + 120 s @ 2000 rpm</p>




Quelle: Hauschild





Results in tabular form – System 1

			no filler	fumed silica	Sillitin V 85	Sillitin Z 86 puriss	Aktisil PF 777	Aktisil Q
Rheology								
Component A	Viscosity @ 0.1 s ⁻¹	Pa·s	17	463	118	213	325	50
	Viscosity @ 100 s ⁻¹		11	22	21	24	21	20
Component A+B	Viscosity @ 0.1 s ⁻¹	Pa·s	7	102	27	59	80	15
	Viscosity @ 100 s ⁻¹		6	9	10	12	12	10
Storage stability Component A								
Sedimentation, 8 w @ RT			-	without	without	without	without	without
Change in rheology, 12 w @ RT				no	no	no	no	no
Mechanical properties								
Lap shear strength Cr3 passivated aluminum, 100 µm		MPa	2.8	3.0	3.4	2.3	3.5	3.1
Peel resistance T-Peel Cr3 passivated aluminum, 100 µm		N / 100 mm	22	20	61	62	70	72




Preparation – System 2

Component A	<p>Speedmixer</p> <p>Resin + first part of filler 30 s @ 800 rpm + rest of filler 30 s @ 800 rpm Clean lid and rim 60 s @ 1000 rpm Clean lid, rim and bottom 300 s @ 2000 rpm</p>
Mixing Component A+B	<p>Speedmixer</p> <p>60 s @ 1000 rpm + 120 s @ 2000 rpm</p>



Quelle: Hauschild





Results in tabular form – System 2

			ungefüllt	Sillitin V 85	Sillitin Z 86 puriss	Aktisil PF 777
Rheology						
Component A	Viscosity @ 0.1 s ⁻¹	Pa·s	1	27	48	138
	Viscosity @ 100 s ⁻¹		1	5	6	9
Component A+B	Viscosity @ 0.1 s ⁻¹	Pa·s	4	12	16	53
	Viscosity @ 100 s ⁻¹		4	9	10	10
Storage stability Component A						
Sedimentation, 8 w @ RT			-	without	without	without
Change in rheology, 12 w @ RT				no	no	no
Mechanical properties						
Lap shear strength Cr3 passivated aluminum, 100 µm		MPa	2.5	3.6	3.3	4.5
Peel resistance T-Peel Cr3 passivated aluminum, 100 µm		N / 100 mm	50	51	39	41



Overview tests

Rheology	MCR 300, PP25, 1 mm gap, 23 °C, logarithmic flow curve from 0.05-500 s ⁻¹ (rotation)
Sedimentation	Storage 8 weeks at room temperature
Application	using a disposable syringe, immediately after mixing the two components
Lap shear strength	<p>DIN EN 1465</p> <p>Substrate: Aluminum 5005 H24 (AlMg1(B)) with Cr3 passivation</p> <p>Adhesive layer: 100 µm, adjusted by 0.2 or 0.5 Vol-% glass beads (on total batch)</p> <p>Curing: 14 days at standard climate 23/50</p> <p>Test speed: 1 mm/min</p> <p>Evaluation: Average maximum stress (tensile shear strength)</p>
T-peel test	<p>DIN EN ISO 11339</p> <p>Substrate: Aluminum 3003 H24 (AlMg1Cu) with Cr3 passivation</p> <p>Adhesive layer: 100 µm, adjusted by 0.2 or 0.5 Vol-% glass beads (on total batch)</p> <p>Curing: 14 days at standard climate 23/50</p> <p>Test speed: 100 mm/min</p> <p>Evaluation: Average peel force, according to standard based on 100 mm sample width</p>