



Neuburg Siliceous Earth Floor Coating based on 2K Polyaspartic

Author: Petra Zehnder

Contents



- Introduction
- Experimental
- Results
- Summary
- Appendix



Status Quo

- Various reactive resin systems are used for durable and resilient floor coatings.
- Environmental and health aspects are becoming increasingly important.
- Modern, low-monomer raw materials can be used to formulate solvent-free coatings with improved workplace hygiene and environmental compatibility.
- Polyaspartic systems offer an additional advantage over other systems in terms of productivity and labor costs thanks to their fast drying time.
- Suitable fillers can help to optimize the formulation and thus improve performance and durability.




Formulations

Component A		parts by weight	
Desmophen NH 1423 LF	Binding agent: aspartic acid ester	16.50	
Sylosiv A4	Desiccant	1.09	
Byk-327	Leveling agent	0.34	
Disperbyk 2205	Wetting/dispersing agent	0.17	
Kronos 2360	White pigment, titanium dioxide	3.44	
Natural barium sulfate	Filler	25.16	---
Neuburg Siliceous Earth	Filler	---	14.87
Desmophen NH 1423 LF	Binding agent: aspartic acid ester	8.21	
Desmophen NH 1723 LF	Reaktive diluent: aspartic acid ester	10.59	
CSTIColor White 6	Pigment paste	3.35	
Total		68.85	58.56
Component B			
Desmodur ultra N 31100	Aliphatic polyisocyanate based on HDI	31.15	
Total A + B		100.00	89.71
Crosslinking ratio NCO/NH	110 %		

Mixing





Filler characteristics

	Particle size		Color CIELab			Oil absorption [g/100g]	Density [g/cm ³]	Specific surface area BET [m ² /g]	Special characteristics - Surface treatment
	d ₅₀ [μm]	d ₉₇ [μm]	L* [-]	a* [-]	b* [-]				
Natural barium sulfate	3.9	16	95.5	-0.1	0.2	13	4.4	1,7	-
Sillitin Z 89	1.9	9	96.1	0.2	4.2	55	2.6	11	-
Sillitin Z 89 puriss	1.9	9	96.1	0.2	4.2	55	2.6	11	improved dispersion properties
Silfit Z 91	2.0	10	96.5	-0.1	1.0	65	2.6	10	calcined
Aktifit AM	2.0	10	96.3	-0.1	1.1	65	2.6	9	calcined, amino functionalized


Structure of Neuburg Siliceous Earth





Viscosity Component A

MCR 300, cylinder system CC27, measurement 7d after preparing




Compared to the control,
the formulations with
Neuburg Siliceous Earth
show

slight increase in viscosity,
especially in the
low shear range




leads to improved storage
stability of component A



Storage stability Component A

4 weeks at room temperature



Compared to the control,
the formulations with
Neuburg Siliceous Earth
show


significantly less phase
separation

markedly reduced sediment



Viscosity A+B

MCR 300, cylinder system CC27



Compared to the control,
the formulations with
Neuburg Siliceous Earth
show


increase in viscosity,
especially in the low shear
range

without significant impairment
of leveling and deaeration



Color CIELab

Measuring geometry d/8°, 300 µm dry film thickness




Compared to the control,
the formulations with
Neuburg Siliceous Earth
show

with **Sillitin**:
slightly higher yellow tint

with **Silfit Z 91 / Aktifit AM**:
comparable color impression




Required film thickness for contrast ratio 98% as indicator hiding power




Compared to the control,
the formulations with
Neuburg Siliceous Earth
need

a significantly lower layer
thickness for
a contrast ratio of 98%

= better hiding power



Gloss




Compared to the control,
the formulations with
Neuburg Siliceous Earth
show

identical gloss




Gloss-haze



Compared to the control,
the formulations with
Neuburg Siliceous Earth
show


lower gloss-haze
= fewer microstructures

Indication of better
compatibility within the
formulation and smaller
particles



Abrasion resistance S 42

DIN 53754, 5.4 N / 100 rev



Compared to the control,
the formulations with
Neuburg Siliceous Earth
show

improved abrasion resistance
against coarser abrasives



Summary

	natural barium sulfate	Sillitin Z 89	Sillitin Z 89 puriss	Silfit Z 91	Aktifit AM
Viscosity	0	↑	↑	↑	↑
Sedimentation	0	++	++	++	++
Processability Deaeration / Leveling	0 / 0	0 / 0	0 / 0	0 / 0	0 / 0
Optical properties Color, Hiding power Gloss, Haze	0 / 0 0 / 0	- / ++ 0 / +	- / ++ 0 / +	0 / ++ 0 / +	0 / ++ 0 / +
Abrasion loss S 42	0	+	+	+	+
Remarks	strong and rapid sediment formation	slight yellow tint	easier to disperse than Sillitin Z 89	color neutral	color neutral, lowest abrasion loss

Benefits of Neuburg Siliceous Earth

significantly less phase separation
+ significantly reduced sediment
= better storage stability

better hiding power

lower gloss-haze

improved abrasion resistance with the calcined grades **Silfit Z 91** and **Aktifit AM**




We supply materials for good ideas!


HOFFMANN MINERAL GmbH
Muenchener Straße 75
DE-86633 Neuburg (Donau)

Phone: +49 8431 53-0
Internet: www.hoffmann-mineral.com
E-mail: info@hoffmann-mineral.com

Our applications engineering advice and the information contained in this memorandum are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.



Neuburg Siliceous Earth




A natural combination of corpuscular Neuburg silica and lamellar kaolinite: a loose mixture impossible to separate by physical methods. The silica portion exhibits a round grain shape and consists of aggregated primary particles of about 200 nm diameter.






Morphology of Neuburg Siliceous Earth






Calcined Neuburg Siliceous Earth

A downstream thermal process leads to the calcined products **SILFIT** and **AKTIFIT**, based on SILLITIN Z 86.



Neuburg Siliceous Earth


Calcination Process
→





Calcined Neuburg Siliceous Earth

Additional application benefits, as well as the removing of crystal water included in the kaolinite. The silica part remains inert.





Preparation

<p>Component A</p>	<p>Dissolver with toothed disc</p> <p>Milling: 15 min @ 11 m/s first part of Desmophen NH 1423 LF, additives, titanium dioxide, filler Target temperature >60 °C (for direct incorporation of Disperbyk 2205)</p> <p>Completion: 5 min @ 4.2 m/s remaining components</p> <p>Allow component A to mature for at least 24 h prior to use.</p>	 <p>Quelle: VMA Getzmann</p>
<p>Mixing A+B</p>	<p>Speedmixer</p> <p>60 s @ 1000 r/min + 120 s @ 2000 r/min</p>	 <p>Quelle: Hauschild</p>






Tests - Overview

Rheology	MCR 300, CC27, 23 °C, flow curve from 0.1-500 s ⁻¹	
Sedimentation	storage 4 weeks at room temperature	
Application	by doctor blade with 510-540 µm gap on Leneta film (results in dry film thickness of approx. 300 µm)	
Drying	at least 3 days in standard climate 23/50	
Color CIELab	X-Rite CI64UV Illuminant D65, normal observer angle 10°, measuring geometry di:8°	
Gloss 20, 60°	Byk micro Tri-Gloss	DIN EN ISO 2813
Gloss-haze	Byk micro haze	
Abrasion resistance	sanding strips S42	DIN 53754, 5.4 N, 100 revolutions




Results in tabular form

			natural barium sulfate	Sillitin Z 89	Sillitin Z 89 puriss	Silfit Z 91	Aktifit AM
Rheology							
Component A	Viscosity @ 0.1 s ⁻¹ Viscosity @ 500 s ⁻¹	Pa·s	1.8 1.4	3.1 1.8	3.1 1.8	2.6 1.9	31 2.0
Component A+B	Viscosity @ 0.1 s ⁻¹ Viscosity @ 500 s ⁻¹	Pa·s	4.2 2.8	8.8 4.2	10.6 4.9	6.8 3.6	5,7 3,6
Storage stability component A, 4 weeks @ room temperature							
Clear supernatant	%		49	2	3	0	0
Sediment	%		14	2	2	5	5
Appearance of sediment	-		hard	soft	soft	soft	very soft
Optical properties							
Color CIELab	L*	-	97.2	95.1	95.0	95.5	95.7
	a*	-	-0.8	-0.4	-0.5	-0.7	-0.7
	b*	-	1.4	4.8	4.7	1.8	1.8
Dry film thickness for contrast ratio 98 %	µm		308	254	250	257	260
Gloss	20° 60	GU	86 93	87 94	87 94	86 94	87 93
Gloss-haze		HU	42	23	26	29	26
Mechanical properties							
Abrasion resistance	S 42	mg	95	70	81	77	68



Abrasion loss CS 17

ASTM D 4060, 1 kg / 1000 rev



Compared to the control,
the formulations with
Neuburg Siliceous Earth
show

under mild stress
slightly higher abrasion with
Sillitin

comparable to slightly
improved abrasion resistance
with the calcined grades
Silfit Z 91 and **Aktifit AM**