


Product	Function	Description	Supplier
3M™ Glass bubbles iM16k	Füllstoff	Hollow glass microspheres	3M
A-C 617	Processing aid	Low molecular weight polyethylene	Honeywell
Aflux 37	Processing aid	Blend of surface active substances with fatty acids	Rhein Chemie
Aflux 42	Processing aid	Water-free blend of fatty acids, fatty alcohols and fatty acid esters	Rhein Chemie
Aflux S	Processing aid	Blend of surface active substances No longer available. Recommended: Aflux 37	Rhein Chemie
Agerite Resin D	Antioxidant	2,2,4-trimethyl-1,2-dihydro-quinoline (TMQ)	Vanderbilt
AKTIFIT AM	Filler	Neuburg Siliceous Earth, calcined, surface treated	HOFFMANN MINERAL
AKTIFIT PF 111	Filler	Neuburg Siliceous Earth, calcined, surface treated	HOFFMANN MINERAL
AKTIFIT PF 115	Filler	Neuburg Siliceous Earth, calcined, surface treated	HOFFMANN MINERAL
AKTIFIT Q	Filler	Neuburg Siliceous Earth, calcined, surface treated	HOFFMANN MINERAL
AKTIFIT VM	Filler	Neuburg Siliceous Earth, calcined, surface treated	HOFFMANN MINERAL
AKTISIL AM	Filler	Neuburg Siliceous Earth, surface treated	HOFFMANN MINERAL
AKTISIL MAM	Filler	Neuburg Siliceous Earth, surface treated	HOFFMANN MINERAL
AKTISIL MAM-R	Filler	Neuburg Siliceous Earth, surface treated	HOFFMANN MINERAL
AKTISIL MM	Filler	Neuburg Siliceous Earth, surface treated	HOFFMANN MINERAL
AKTISIL PF 216	Filler	Neuburg Siliceous Earth, surface treated	HOFFMANN MINERAL
AKTISIL PF 777	Filler	Neuburg Siliceous Earth, surface treated	HOFFMANN MINERAL
AKTISIL Q	Filler	Neuburg Siliceous Earth, surface treated	HOFFMANN MINERAL
AKTISIL VM 56	Filler	Neuburg Siliceous Earth, surface treated	HOFFMANN MINERAL
AKTISIL VM 56/89	Filler	Neuburg Siliceous Earth, surface treated	HOFFMANN MINERAL




Product	Function	Description	Supplier
Alcanpoudre DBU-70	Activator	DBU 1,8-Diazabicyclo[5.4.0]undec-7-ene	Safic-Alcan
Alcanplast PO 80	Plasticizer	Ether-ester-plasticizer	Safic-Alcan
Aluminium hydroxide	Flame retardant, filler	Al(OH) <sub>3</sub>	several
Anox PP 18	Antioxidant	Sterically hindered phenol	Chemtura
Antilux 110	Antiozonant	Micro crystalline wax	Rhein Chemie
Antilux 500 L	Antiozonant	Micro crystalline wax	Rhein Chemie
Antimony oxide	Flame retardant	Sb <sub>2</sub> O <sub>3</sub>	several
Antioxidant HS	Antioxidant	2,2,4-trimethyl-1,2-dihydro-quinoline (TMQ)	several
Antioxidant MB	Antioxidant	Mercapto-benzimidazole (MBI)	several
Antioxidant PBN	Antioxidant	Phenyl-beta-naphtylamine	several
AOX 2246	Antioxidant	2,2-methylene-bis (4-methyl-6-tert.-butylphenol (BPH)	several
APF N-683	Filler	Carbon black	several
Apyral 40 CD	Flame retardant, filler	Aluminium hydroxide, ATH, Al(OH) <sub>3</sub>	Nabaltec
Argiflex No. 2	Filler	Hard clay, surface treated No longer available.	AGS Mineraux
Argirec KN 20	Filler	Hard clay, surface treated	AGS Mineraux
Armeen 18D	Processing aid	n-Octadecylamine	Nouryon
Atactic polybutene	Polymeric plasticizer	Isobutylene	several
Barite	Filler	Natural barium sulfates	several
Barium sulfate	Filler	BaSO <sub>4</sub>	several
Baypren 110	Polymer	CR	Arlanxeo
Baypren 210	Polymer	CR	Arlanxeo
Baypren 214	Polymer	CR	Arlanxeo
Baypren 230	Polymer	CR	Arlanxeo
Baypren 611	Polymer	CR	Arlanxeo
Benzoic acid	Cure retarder		several
Blanc Fixe	Filler	Precipitated barium sulfate (BaSO <sub>4</sub> )	Venator Materials Corporation
Blowing agent BSH	Blowing agent	Benzene sulfohydrazide	several
Buna AP 147	Polymer	EPDM No longer available. Recommended: Keltan 2470	




Product	Function	Description	Supplier
Buna AP 258	Polymer	EPDM No longer available. Recommended: Keltan 3973	
Buna AP 341	Polymer	EPDM No longer available. Recommended: Keltan 4450	
Buna AP 344	Polymer	EPDM, oil extended No longer available. Recommended: Keltan 4455	
Buna AP 447	Polymer	EPDM No longer available. Recommended: Keltan 5470 or Keltan 5470Q	
Buna AP 451	Polymer	EPDM No longer available. Recommended: Keltan 6750	
Buna AP 541	Polymer	EPDM No longer available. Recommended: Keltan 7450	
Buna CB 10	Polymer	BR No longer available. Recommended: Buna CB 24	
Buna CB 11	Polymer	BR No longer available. Recommended: Buna CB 24	
Buna CB 24	Polymer	BR	Arlanxeo
Buna CIS 132 - Schokpau	Polymer	BR	Trinseo
Buna EP G 3569 LF	Polymer	EPDM, oil extended No longer available. Recommended: Keltan 4577 + 25 phr paraffin oil	
Buna EP G 6850	Polymer	EPDM No longer available. Recommended: Keltan 6750	
Buna SB 1502	Polymer	Cold polymerised emulsion styrene butadiene rubber (E-SBR)	Trinseo
Butyl 268	Polymer	IIR	ExxonMobil Chemical
Butyl Zimate	Accelerator	Zinc-dibutyl-dithiocarbamate (ZDBC)	Vanderbilt
Cab-O-Sil M-7D	Filler	Pyrogenic silica, 200 m <sup>2</sup> /g	Cabot




Product	Function	Description	Supplier
Calcined clay	Filler	Dehydrated clay	several
Calcium hydroxide	Activator		several
Calcium oxide	Desiccant	CaO	several
Calcium oxide xx %	Desiccant	CaO in mineral oil and wax	several
Caldic PIB V 190	Plasticizer	Polyisobutene	Caldic
Caloxol	Desiccant	CaO in mineral oil	Omya UK Chemicals
Caloxol W3	Desiccant	75 % CaO in mineral oil and wax	Omya UK Chemicals
Carbon Black N-550	Filler	Carbon black	several
Carbon Black N-774	Filler	Carbon black	several
Carbon Black N-990	Filler	Carbon black	several
Carbon Black SRF	Filler	Carbon black	several
Carbowax PEG 4000	Filler activator	Polyethylene glycol	Dow Chemical Company
CBS	Accelerator	Cyclohexyl-benzothiazyl-sulfenamide	several
Celogen OT	Blowing agent	Oxy-bis (benzene-sulfohydrazide)	Lion Copolymer
Chimassorb 944	Antioxidant	Sterically hindered amine	BASF
China Clay	Filler	Soft clay	Imerys Performance Minerals
Chlorinated paraffin 70 %	Flame retardant, plasticizer	Chlorinated paraffin (70 % chlorine)	several
Chlorinated paraffin liquid	Flame retardant, plasticizer		several
Corax N 330	Filler	Carbon black	Orion Engineered Carbons
Corax N 550	Filler	Carbon black	Orion Engineered Carbons
Corax N 550/30	Filler	Carbon black	Orion Engineered Carbons
Corax N 650	Filler	Carbon black	Orion Engineered Carbons
Corax N 774	Filler	Carbon black	Orion Engineered Carbons
Cortis 100 M	Plasticizer	Paraffin oil	Total
Coupsil 6411	Filler	Precipitated silica, silane treated	Evonik Industries
Coupsil 8415	Filler	Precipitated silica, silane treated No longer available. Recommended: Coupsil based on Ultrasil VN3 treated with 15 % thiocyanato-silane	Evonik Industries
Crodamide ER	Processing aid	Erucamide	Croda
Crodamide SR	Processing aid	Stearyl amide	Croda
Crystex	Curing agent	Insoluble sulfur	Eastman




Product	Function	Description	Supplier
CSM	Polymer	Chlorsulfonated polyethylene	several
CTP (PVI)	Cure retarder	Cyclohexyl-thiophthalimide	several
DBTU	Accelerator	Dibutyl-thiourea	several
DCP 40 %	Curing agent	Dicumyl peroxide	several
DDTS	Accelerator	Dimethyl-diphenyl-thiuram-disulfide	several
Deovulc BG 187	Accelerator	Synergistic blend of thiazol, dithiophosphate and alkaline accelerators	DOG-Chemie
Deovulc EG 28	Accelerator	Synergistic blend of effective accelerators, ETU-free, contains sulfur donor	DOG-Chemie
DHBP 40 %	Curing agent	2,5-dimethyl-2,5-di (tert.-butyl-peroxy) hexane	several
Diak No. 1	Curing agent	Hexamethylenediamine carbamate	DuPont
Diak No. 7	Co-agent for peroxide cure	Triallyl isocyanurate	DuPont
Diethylene glycol	Filler activator		several
Dioctyl phthalate	Plasticizer		several
Disflamoll DPK	Plasticizer	Diphenyl-kresyl-phosphate	Lanxess
Dispergator DS	Processing aid	Emulsion of higher alcohols, esters and fatty acids	Kettlitz-Chemie
Dispergator FL	Processing aid	Blend of metal soaps, high boiling alcohols and fatty acids	Kettlitz-Chemie
Dixie Clay	Filler	Hard clay	Vanderbilt
DNPT	Blowing agent	Dinitroso-pentamethylene-tetramine	several
DOTG	Accelerator	Di-o-tolyl-guanidine	several
DPG	Accelerator	Diphenyl-guanidine	several
DPTH	Accelerator	Dipentamethylen-thiuram-hexasulfide	several
DTDM	Accelerator	Dithiomorpholine	several
Duranit B	Reinforcing resin	High styrene resin (60 % HSR) No longer available. Recommended: Europrene HS 630	
Durex 0	Filler	Carbon black (similar to N-660)	Orion Engineered Carbons
Dutral TER 4436	Polymer	EPDM, oil extended	Polimeri Europa
Dutral TER 6235	Polymer	EPDM, oil extended	Polimeri Europa
Dynasylan AMEO	Coupling agent	3-Aminopropyl-triethoxy-silane	Evonik Industries
Dyneon FC 2181Z	Polymer	FKM	3M



Product	Function	Description	Supplier
Ebrosil SA 60	Filler	Sodium and aluminum silicate, precipitated and amorphous	Industrias Quimicas del Ebro
Edenol T810T	Plasticizer	Trimellitate of linear C8-and C10-alcohols	Safic-Alcan
EDMA	Co-agent for peroxide cure	Ethylene glycol dimethacrylate	several
Elastomag 170	Activator	Magnesium oxide	several
Elastosil AUX Batch PT 2	Catalyst	Platinum catalyst masterbatch	Wacker Chemie
Elastosil AUX Curing Agent C6	Curing agent	2,5-bis-(tert.-butylperoxo)-2,5-dimethylhexane, 45 % in silicone rubber	Wacker Chemie
Elastosil AUX Curing Agent E	Curing agent	Bis-(2,4-dichlorbenzoyl-) peroxide, 50 % in silicone oil	Wacker Chemie
Elastosil R 401/30	Polymer	Q (high consistency silicone rubber)	Wacker Chemie
Elastosil R 401/40	Polymer	Q (high consistency silicone rubber)	Wacker Chemie
Elastosil R 401/50	Polymer	Q (high consistency silicone rubber)	Wacker Chemie
Elastosil R 420/40	Polymer	Q (high consistency silicone rubber)	Wacker Chemie
Elastosil R 420/50	Polymer	Q (high consistency silicone rubber)	Wacker Chemie
Elastosil R 752/50	Polymer	Q (high consistency silicone rubber)	Wacker Chemie
Elastosil R 752/70	Polymer	Q (high consistency silicone rubber)	Wacker Chemie
Elastosil R plus 4000/40 MH	Polymer	Q (high consistency silicone rubber)	Wacker Chemie
Ethyl Tellurac	Accelerator	Tellurium-diethyl-dithiocarbamate (TDEC)	Vanderbilt
ETU	Accelerator	Ethylene-thiourea (2-mercaptoimidazoline)	several
Europrene HS 630	Reinforcing resin	Resin rubber masterbatch, coagulating a blend of a high styrene resin latex and SBR latex (63 % styrene)	Versalis
Europrene OZO N 7033	Polymer	Blend of acrylonitrile-butadiene copolymer and polyvinyl chloride in the ratio 70/30	Versalis
Europrene N 3360	Polymer	NBR	Versalis
Europrene SOL B 1205	Polymer	Solution styrene-butadiene partial block copolymer, polymerized using an alkyl lithium catalyst	Versalis



Product	Function	Description	Supplier
Evolute N 375 (ex Sunthene 4240)	Plasticizer	Naphthenic mineral oil	Petronas
Expancel 950 DU 80	Blowing agent	Microspheres	Nouryon
Exxon Butyl 365	Polymer	IIR	ExxonMobil Chemical
Factice	Processing aid	Sulfur vulcanized vegetable oil	several
Faktis DS weich	Processing aid	Sulfur vulcanized vegetable oil with addition of mineral oil	DOG-Chemie
Faktis RC 141	Processing aid	Sulfur vulcanized vegetable oil No longer available. Recommended: Rhenopren 14	
Faktogel Rheinau H	Processing aid	Sulfur chloride factice white No longer available. Recommended: Rhenopren EPS	
FEF N-539	Filler	Carbon black	several
FEF N-550	Filler	Carbon black	several
First Latex Crepe	Polymer	NR	several
Flectol H	Antioxidant	2,2,4-trimethyl-1,2-dihydro-quinoline (TMQ) No longer available. Recommended: Vulkanox HS/LG	
Geniosil GF 58	Coupling agent	Vinyl-tris (methoxy-ethoxy) silane	Wacker Chemie
Genitron AC2	Blowing agent	Azodicarbonamide	several
Genitron AC4	Blowing agent	Azodicarbonamide (Porofor ADC/M-C1)	several
Genitron ACR	Blowing agent	Azodicarbonamide / toluenesulfohydrazide	Lanxess
Genitron CR	Blowing agent	Composition undisclosed, decomposition temperature 160-190°C	several
Genitron OB	Blowing agent	Oxy-bis (benzenesulfonyl hydrazide) (OBSh)	Lanxess
GLOXIL iM16k MAM	Filler	Hollow glass microspheres, surface treated	HOFFMANN MINERAL
GPF N-650	Filler	Carbon black	several
GPF N-660	Filler	Carbon black	several
Grundöl AP/E Core 2500	Plasticizer	Paraffin oil, high viscosity (ex Flexon 815)	ExxonMobil Chemical
Grundöl AP/E Core 600	Plasticizer	Paraffin oil, medium viscosity (ex Flexon 876)	ExxonMobil Chemical
Gulf Oil 2212	Plasticizer	Paraffin oil	Gulf



Product	Function	Description	Supplier
HAF	Filler	Carbon black N-330	several
HAF N-330	Filler	Carbon black	several
Hansa Dis T4	Processind aid	Lignosulphonates and derivates	Sappi Biotech
Hard clay	Filler		several
Hatcol 200	Plasticizer	Tris(2-ethylhexyl)trimellitate (TOTM)	Lanxess
HVA Nr. 2	Accelerator	N,N'-m-phenylene dimaleimide	several
ImerFlex T10	Filler	Talc	Imerys Talc
ImerFlex T10C	Filler	Talc	Imerys Talc
Irganox 1010	Antioxidant	Sterically hindered phenol	BASF
Irganox 1076	Antioxidant	Sterically hindered phenol	BASF
Iron oxide red	Pigment	Iron oxide	several
Jayflex DINA	Plasticizer	Di-isononyl-adipate	ExxonMobil Chemical
Kagevest 25	Coupling agent	Low molecular polybutadiene with silizium alkoxy-groups (ex Polyvest 25)	Schirm
Keltan 312	Polymer	EPDM No longer available. Recommended: Keltan 2450	
Keltan 509x100	Polymer	EPDM, oil extended No longer available. Recommended: Keltan 4869	
Keltan 512	Polymer	EPDM No longer available. Recommended: Keltan 4450	
Keltan 512x50	Polymer	EPDM, oil extended No longer available. Recommended: Keltan 4450 + 50 phr paraffin oil	
Keltan 578Z	Polymer	EPDM No longer available. Recommended: Keltan 5470 or Keltan 5470Q	
Keltan 708x15Z	Polymer	EPDM, oil extended No longer available. Recommended: Keltan 6471	
Keltan 712	Polymer	EPDM No longer available. Recommended: Keltan 6460D or Keltan 6950	







Product	Function	Description	Supplier
Keltan 778Z	Polymer	EPDM No longer available. Recommended: Keltan 5470C	
Keltan 2450	Polymer	EPDM	Arlanxeo
Keltan 2470	Polymer	EPDM	Arlanxeo
Keltan 2650	Polymer	EPDM	Arlanxeo
Keltan 3960Q	Polymer	EPDM	Arlanxeo
Keltan 3973	Polymer	EPDM	Arlanxeo
Keltan 4450	Polymer	EPDM	Arlanxeo
Keltan 4450S	Polymer	EPDM	Arlanxeo
Keltan 4455	Polymer	EPDM, oil extended	Arlanxeo
Keltan 4577	Polymer	EPDM, oil extended	Arlanxeo
Keltan 4869	Polymer	EPDM, oil extended	Arlanxeo
Keltan 5465Q	Polymer	EPDM, oil extended	Arlanxeo
Keltan 5469	Polymer	EPDM, oil extended	Arlanxeo
Keltan 5469Q	Polymer	EPDM, oil extended	Arlanxeo
Keltan 5470C	Polymer	EPDM	Arlanxeo
Keltan 5470Q	Polymer	EPDM	Arlanxeo
Keltan 6460D	Polymer	EPDM	Arlanxeo
Keltan 6471	Polymer	EPDM, oil extended	Arlanxeo
Keltan 6750	Polymer	EPDM	Arlanxeo
Keltan 6950	Polymer	EPDM	Arlanxeo
Keltan 7450	Polymer	EPDM	Arlanxeo
Keltan 8340A	Polymer	EPDM No longer available. Recommended: Keltan 8550	
Keltan 8550C	Polymer	EPDM	Arlanxeo
Kezadol GR	Desiccant	CaO, coated by special dispersing agents	Kettlitz-Chemie
Ketjenblack EC-600JD	Filler	electroconductive carbon black	Nouryon
Koresin	Tackifying agent	Butylphenol-acetylene-resin	BASF
Kronos 2056	White pigment	Titanium dioxide, rutile	Kronos International
Kronos 2222	White pigment	Titanium dioxide, rutile	Kronos International




Product	Function	Description	Supplier
Krylene HS 260	Reinforcing resin	High styrene resin (65 % styrene) No longer available. Recommended: Europrene HS 630	
Krynac 2950 F	Polymer	NBR, 30 % ACN No longer available. Recommended: NBR, 30 % ACN, ML 1+4 (100°C) 53 MU	
LDPE LD 653	Processing aid	Low density polyethylene, MFR 22 g/10 min	ExxonMobil Chemical
Lipoxol 3000	Filler activator	Polyethylene glycol	Sasol Olefins & Surfactants
Lipoxol 4000	Filler activator	Polyethylene glycol	Sasol Olefins & Surfactants
Lipoxol 6000	Filler activator	Polyethylene glycol	Sasol Olefins & Surfactants
Litharge	Activator	PbO	several
Luperox 101XL45	Curing agent	2,5-dimethyl-2,5-di-(t-butylperoxy)- hexane, 45 %	Arkema
Luperox 130XL45	Curing agent	2,5-dimethyl-2,5-bis-(t-butylperoxy)- hexin-3, 45 %	Arkema
Luperox F40	Curing agent	Bis-(t-butylperoxy-i-propyl) benzene, 40 %	Arkema
Luvomaxx CDPA	Antioxidant	4, 4'-bis-(1,1-dimethylbenzyl)- diphenylamine	Lehmann & Voss
Luvomaxx Safecure CA	Co-agent	Composition of aliphatic amines	Lehmann & Voss
Maglite DE	Activator	MgO	HallStar
Magnesium hydroxide	Flame retardant		several
Magnesium oxide	Activator	MgO	several
Magnesium oxide light	Activator	MgO	several
Martinal OL-111 LE	Filler	Al(OH) <sub>3</sub>	Albemarle (Martinswerk)
MBT	Accelerator	Mercapto-benzothiazole	several
MBTS	Accelerator	Dibenzo-thiazyl-disulfide	several
Mediaplast EP-P	Plasticizer	Polyalkylbenzene No longer available. Recommended: Mediaplast PX-2	
Mediaplast NB 4	Plasticizer	Special adipine acid ester	Kettlitz-Chemie
Mediaplast NB 500	Plasticizer	Phthalate-free ester blend	Kettlitz-Chemie




Product	Function	Description	Supplier
Mediaplast PX-2	Plasticizer	Semi-synthetic paraffin based hydrocarbon	Kettlitz-Chemie
Mediaplast WH	Tackifying agent, processing aid	Aromatic resin	Kettlitz-Chemie
Mesamoll	Plasticizer	Phenol alkylsulfonic acid ester	Lanxess
Mikrosöhl 40	Filler	Whiting	Vereinigte Kreidewerke Damman
Mistrobond R10C	Filler	Talc, surface treated	Imerys Talc
Mistron Vapor	Filler	Talc No longer available. Recommended: ImerFlex T10C	
MMBI	Antioxidant	Methyl-mercapto-benzimidazole	several
Mold Wiz INT-44/3PV	Internal release and lubricating agent	Proprietary blend of synthetic resins and fatty glycerides with modified organic fatty acids	Axel Plastics Research Laboratories
MT N-990	Filler	Carbon black	several
Naphthenic oil	Plasticizer		several
Naugard 445	Antioxidant	Substituted diphenylamine	Chemtura
Naugex MBT	Accelerator	Mercapto-benzothiazole	Chemtura
NBR, 34 % ACN	Polymer	NBR	several
NDBC	Stabilizer	Nickel-dibutyldithiocarbamate	several
Neoprene W	Polymer	CR, mercaptan type	DuPont
Neoprene WHV	Polymer	CR, mercaptan type	DuPont
Nipol 1042	Polymer	NBR	Zeon Europe
Norsolene S 85	Tackifying agent	Aromatic resin	Cray Valley
Norsolene S 105	Tackifying agent	Aromatic resin	Cray Valley
Norsolene S 155	Tackifying agent	Aromatic resin	Cray Valley
Norsorex 150 NA	Polymer	Polynorbonene, oil extended	Astrotech Advanced Elastomerproduct
Norsorex 150 NA 25 EP	Polymer	Blend of polynorbonene and EPDM, oil extended	Astrotech Advanced Elastomerproduct
Novares C 90	Processing aid	Cumaron-inden-resin, softening point approx. 90°C	Rain Carbon
NR	Polymer	NR	several
NR Smoked Sheets	Polymer	NR	several
NR SMR 20	Polymer	NR	several
Nytex 4700	Plasticizer	Naphthenic oil	Nynas




Product	Function	Description	Supplier
OBSH	Blowing agent	Oxy-bis (benzenesulfonyl hydrazide)	several
Ofalub SEO	Processing aid	Phosphoric acid ester of modified fatty alcohols	Safic-Alcan
Oleamide	Processing aid		several
Omya BL	Filler	Whiting	Omya
Omya BSH	Filler	Whiting, surface treated	Omya
Omya EX H1	Filler	Whiting	Omya
Paraffin oil	Plasticizer		several
Paraffin wax	Processing aid		several
PAT 44/04	Processing aid	Fatty acid salts	Würtz
Pb <sub>3</sub> O <sub>4</sub> 80 %	Crosslinking agent, stabilizer		several
PEG 3000	Filler activator	Polyethylene glycol	several
PEG 3350	Filler activator	Polyethylene glycol	several
PEG 3400	Filler activator	Polyethylene glycol	several
PEG 4000	Filler activator	Polyethylene glycol	several
PEG 6000	Filler activator	Polyethylene glycol	several
Perbunan 3307	Polymer	NBR, 34 % ACN No longer available. Recommended: Perbunan 3945 F or Perbunan 3946 F	
Perbunan 3807 NS	Polymer	NBR, 38 % ACN No longer available. Recommended: Perbunan 3945 F	
Perbunan 3445 F	Polymer	NBR, 34 % ACN	Arlanxeo
Perbunan 3446 F	Polymer	NBR, 34.7 % ACN	Arlanxeo
Perbunan 3945 F	Polymer	NBR, 39 % ACN	Arlanxeo
Perkacit TBzTD	Accelerator	Tetrabenzyl-thiuram-disulfide	Performance Additives
Perkacit TDEC	Accelerator	Tellurium-diethyl-dithiocarbamate	Performance Additives
Perkacit ZBEC	Accelerator	Zinc-dibenzyl-dithiocarbamate	Performance Additives
Perkacit ZDBC	Accelerator	Zinc-dibutyl-dithiocarbamate	Performance Additives
Perkacit ZDEC	Accelerator	Zinc-diethyl-dithiocarbamate	Performance Additives
Perkadox 14-40	Curing agent	Bis (t-butylperoxy-i-propyl) benzene, 40 %	Nouryon
Perkadox 14-40B	Curing agent	Bis (t-butylperoxy-i-propyl) benzene, 40 % bound to whiting and silica	Nouryon




Product	Function	Description	Supplier
Perkadox 14-40MB	Curing agent	Bis (t-butylperoxy-i-propyl) benzene, 40 % polymer bound	Nouryon
Perkadox BC-40S	Curing agent	Dicumyl peroxide, paste 40 % in silicone oil	Nouryon
Perkadox BC-FF	Curing agent	Dicumyl peroxide	Nouryon
Perkadox PD-50S-PS	Curing agent	Di(2,4-dichlorobenzoyl) peroxide DCBP paste 50% active ingredient in silicone oil and silica	Nouryon
Perkadox PM-50S-PS	Curing agent	Di(4-methylbenzoyl) peroxide DMBP paste 50% active ingredient in silicone oil and silica	Nouryon
Perkasil KS 300	Filler	Precipitated silica, 130 m <sup>2</sup> /g	Grace
Perkasil KS 408	Filler	Precipitated silica, 175 m <sup>2</sup> /g	Grace
Phenodur EP 560	Crosslinking resin	Phenolic resin	Allnex
Polestar 200R	Filler	Calcined clay	Imerys Performance Minerals
Polybutadiene BR 1220	Polymer	BR	several
Polydispersion E (VC) D-40	Curing agent	Bis (t-butylperoxy-i-propyl) benzene, 40 %	Omya (Croxtton & Garry)
Polyethylene glycol	Filler activator		several
Polyethylene wax	Processing aid		several
Polyplastol 6	Processing aid	Zinc salt of fatty acids	Elastomeri Polimeri
Polysar EPDM 346	Polymer	EPDM No longer available. Recommended: Keltan 2470	
Polysar EPDM 585	Polymer	EPDM No longer available. Recommended: Keltan 3960Q	
Polysar EPDM 5465	Polymer	EPDM, oil extended No longer available. Recommended: Keltan 5469Q	
Polysar EPDM 5875	Polymer	EPDM, oil extended No longer available. Recommended: Keltan 4869	



Product	Function	Description	Supplier
Polysar EPDM 6463	Polymer	EPDM, oil extended No longer available. Recommended: Keltan 5465Q	
Porofor TSH	Blowing agent	Toluene sulfohydrazide	Lanxess
Primol 352	Plasticizer	White oil (medical grade)	ExxonMobil Chemical
Process Oil P 100 (ex Sunpar 150)	Plasticizer	Paraffinic mineral oil	Petronas
Process Oil P 460 (ex Sunpar 2280)	Plasticizer	Paraffinic mineral oil	Petronas
Protektor G 35 P	Antiozonant	Micro crystalline wax	Paramelt
Protektor G 3108	Antiozonant	Micro crystalline wax	Paramelt
Protektor G 3888	Antiozonant	Micro crystalline wax	Paramelt
Purex HS 45	Filler	Carbon black	Orion Engineered Carbons
Quartz sand	Filler		several
Resin	Processing aid		several
Rhenocure CA	Accelerator	Diphenyl-thiourea	Rhein Chemie
Rhenocure Thiuram MS	Accelerator	Tetramethyl thiurame monosulfide (TMTM)	Rhein Chemie
Rhenocure TP/S	Accelerator	Zinc-dialkyl-dithiophosphate, 67 % bound to silica	Rhein Chemie
Rhenofit C	Desiccant	CaO	Rhein Chemie
Rhenofit DDA	Antioxidant	Styrenated diphenylamine	Rhein Chemie
Rhenofit EDMA/S	Co-agent for peroxide cure	Ethylen glycol-dimethacrylate, 70 % bound to silica	Rhein Chemie
Rhenofit OCD	Antioxidant	Octylated diphenylamine (ODPA)	Rhein Chemie
Rhenofit TAC/S	Co-agent for peroxide cure	Triallyl cyanurate, 70 % bound to silica	Rhein Chemie
Rhenofit TRIM/S	Co-agent for peroxide cure	Trimethylol-propane-trimethacrylate, 70 % bound to silica	Rhein Chemie
Rhenogran ADT-50	Accelerator	Amino dithiophosphate, 50 % polymer bound	Rhein Chemie
Rhenogran CaO-80	Desiccant	80 % CaO, surface treated	Rhein Chemie
Rhenogran CBS-80	Accelerator	Cyclohexyl-benzothiazyl-sulfenamide, 80 % polymer bound	Rhein Chemie
Rhenogran CLD-80	Accelerator	Dithio-caprolactam, 80 % polymer bound	Rhein Chemie



Product	Function	Description	Supplier
Rhenogran CUT-50	Accelerator	Copper-dialkyl-dithiophosphate, 50 % polymer bound	Rhein Chemie
Rhenogran DPG-80	Accelerator	Diphenyl-guanidine, 80 % polymer bound	Rhein Chemie
Rhenogran DTDM-80	Accelerator	4,4'-dithio-dimorpholine, 80 % polymer bound	Rhein Chemie
Rhenogran ETU-80	Accelerator	Ethylene-thiourea, 80 % polymer bound	Rhein Chemie
Rhenogran Geniplex-70	Accelerator	Zinc-dicyanato-diamine, 70 % polymer bound	Rhein Chemie
Rhenogran MBT-80	Accelerator	Mercapto-benzothiazole, 80 % polymer bound	Rhein Chemie
Rhenogran MBTS-80	Accelerator	Dibenzo-thiazyl-disulfide, 80 % polymer bound	Rhein Chemie
Rhenogran P 50	Hydrolysis stabilizer	50 % polycarbodiimide / 50 % ethylene-vinylacetate-copolymer No longer available. Recommended: Rhenogran PCD-50/EVA	
Rhenogran PCD-50/EVA	Hydrolysis stabilizer	50 % polycarbodiimide / 50 % ethylene-vinylacetate-copolymer / SiO <sub>2</sub>	Rhein Chemie
Rhenogran S-80	Curing agent	Sulfur	Rhein Chemie
Rhenogran TBBS-80	Accelerator	N-tert.-butyl-2-benzothiazyl sulfenamide, 80 % polymer bound	Rhein Chemie
Rhenogran TBzTD-70	Accelerator	Tetrabenzyl-thiuram-disulfide, 70 % elastomer bound	Rhein Chemie
Rhenogran TMTD-70	Accelerator	Tetramethyl-thiuram-disulfide, 70 % polymer bound	Rhein Chemie
Rhenogran TMTM-80	Accelerator	Tetramethyl-thiuram-monosulfide, 80 % polymer bound	Rhein Chemie
Rhenogran TP-50	Accelerator	Zinc-dialkyl-dithiophosphate, 50 % polymer bound	Rhein Chemie
Rhenogran ZAT-70	Accelerator	Zinc-amine-dithiophosphate-complex, 70 % polymer bound	Rhein Chemie
Rhenogran ZBEC-70	Accelerator	Zinc-dibenzyl-dithiocarbamate, 70 % polymer bound	Rhein Chemie
Rhenogran ZDBC-80	Accelerator	Zinc-dibutyl-dithiocarbamate, 80 % polymer bound	Rhein Chemie



Product	Function	Description	Supplier
Rhenogran ZMMBI-50	Antioxidant	Zinc-methyl-mercaptop-benzimidazole, 50 % polymer bound	Rhein Chemie
Rhenopren 14	Processing aid	Sulfur vulcanized vegetable oil	Rhein Chemie
Rhenopren EPS	Processing aid	Sulfur and chlorine-free vulcanized vegetable oils	Rhein Chemie
Rhenosin W 759	Plasticizer	Ether/ester-compound	Rhein Chemie
Ribbed Smoked Sheets RSS1	Polymer	NR	several
SABIC LLDPE 0132HS00	Processing aid	Medium density polyethylene, MFR 0,8 g/10 min	Sabic
Sachtleben R-KB-2	White pigment	Titanium dioxide, rutile No longer available. Recommended: Titanium dioxide R-KB-2	
Sachtleben R-U-5	White pigment	Titanium dioxide, rutile	Venator Materials Corporation
Safic-Chem OMB	Antioxidant	2,2'-Methylene-bis(4-methyl-6-tert. butylphenol)	Safic Alcan
Saret SR-517	Co-agent for peroxide cure	Trimethacrylate ester (retarded)	Sartomer
Sartomer SR-206	Co-agent for peroxide cure	Ethylene glycol-dimethacrylate (EDMA)	Sartomer
Sartomer SR-350	Co-agent for peroxide cure	Trimethylol-propane-trimethacrylate (TRIM, TMPT)	Sartomer
SBR	Polymer		several
SBR 1502	Polymer	SBR	several
SBR 4684	Polymer	Developmental carbon black master batch (CBMB) containing 52 parts of N-234 carbon black, extended with 10 parts of highly aromatic oil. Product is made on demand.	Lion Elastomers
Scorchguard O	Activator	Magnesium oxide dispersion	Rhein Chemie
Shell Gravex Oil 921	Plasticizer	Naphthenic mineral oil	Shell
Si 69	Coupling agent	Bis-(triethoxy-silyl-propyl)-tetra- sulfane	Evonik Industries
Sikron SF 600	Filler	Quartz flour	Quarzwerte
Silanogran PV	Coupling agent	50 % granules of a trimethoxy- silylgroup containing low molecular polybutadiene	Kettlitz-Chemie






Product	Function	Description	Supplier
Silanogran VES	Coupling agent	50 % granules of triethoxy-vinyl silane with oligomeric alkyl groups	Kettlitz-Chemie
Silica	Filler		several
SILFIT Z 91	Filler	Neuburg Siliceous Earth, calcined	HOFFMANN MINERAL
SILLIKOLLOID P 87	Filler	Neuburg Siliceous Earth	HOFFMANN MINERAL
SILLITIN N 75	Filler	Neuburg Siliceous Earth	HOFFMANN MINERAL
SILLITIN N 82	Filler	Neuburg Siliceous Earth No longer available. Recommended: SILLITIN N 75	
SILLITIN N 85	Filler	Neuburg Siliceous Earth	HOFFMANN MINERAL
SILLITIN V 85	Filler	Neuburg Siliceous Earth	HOFFMANN MINERAL
SILLITIN V 88	Filler	Neuburg Siliceous Earth	HOFFMANN MINERAL
SILLITIN Z 86	Filler	Neuburg Siliceous Earth	HOFFMANN MINERAL
SILLITIN Z 86 PURISS	Filler	Neuburg Siliceous Earth	HOFFMANN MINERAL
SILLITIN Z 89	Filler	Neuburg Siliceous Earth	HOFFMANN MINERAL
Silquest A-172NT	Coupling agent	Vinyl-tris (methoxy-ethoxy) silane	Momentive Performance Materials
Silquest A-189	Coupling agent	Mercaptopropyl-trimethoxy silane	Momentive Performance Materials
Silquest RC-1	Coupling agent	vinyl-organofunctional silane	Momentive Performance Materials
SMR 5	Polymer	NR	several
SMR CV 50	Polymer	NR, constant viscosity	several
SMR CV 60	Polymer	NR, constant viscosity	several
SP-1056	Crosslinking resin	Brominated octylphenol resin (heat reactive)	SI Group (ex Schenectady)
Speswhite	Filler	Soft clay	Imerys Performance Minerals
Spheron 5000	Filler	Carbon black	Cabot
SRF N-762	Filler	Carbon black	several
SRF N-765	Filler	Carbon black	several
SRF N-770	Filler	Carbon black	several
SRF N-774	Filler	Carbon black	several
Stearic acid	Processing aid, activator		several
Sterically hindered phenol	Antioxidant		several




Product	Function	Description	Supplier
Struktol Activator 73	Activator	Blend of zinc soaps of aliphatic and aromatic carboxylic acids	Schill + Seilacher
Struktol AW 1	Antistatic plasticizer	Polyethylene glycol ester	Schill + Seilacher
Struktol KW 326	Plasticizer	Synthetic ester plasticizer	Schill + Seilacher
Struktol KW 460	Plasticizer	Polyglycol ester	Schill + Seilacher
Struktol KW 759	Plasticizer	Aliphatic ether/ester	Schill + Seilacher
Struktol SU 109	Curing agent	Preparation of insoluble sulfur, 75 %	Schill + Seilacher
Struktol SU 135	Curing agent	Preparation of insoluble sulfur, 75 %	Schill + Seilacher
Struktol TS 30	Tackifying agent	Aliphatic / aromatic soft resin	Schill + Seilacher
Struktol TS 30-DL	Tackifying agent	Aliphatic / aromatic soft resin	Schill + Seilacher
Struktol TS 35	Tackifying agent	Aliphatic / aromatic soft resin	Schill + Seilacher
Struktol WB 16	Processing aid	Blend of soaps of fatty acids	Schill + Seilacher
Struktol WB 212	Processing aid	Blend of fatty acid esters and water, bound to filler	Schill + Seilacher
Struktol WB 217	Processing aid	Blend of fatty acid esters	Schill + Seilacher
Struktol WB 222	Processing aid	Ester of saturated fatty acids	Schill + Seilacher
Struktol WB 300 A	Plasticizer	Synthetic ester	Schill + Seilacher
Struktol WB 902	Activator	Magnesium oxide preparation	Schill + Seilacher
Struktol WS 180	Processing aid	Silicone / fatty acid derivate condensation product	Schill + Seilacher
Struktol WS 280	Processing aid	Organosilicone compound, bound to anorganic carrier	Schill + Seilacher
STRUKTOSIL 45 AM	Filler	Talc, surface treated	HOFFMANN MINERAL
STRUKTOSIL 45 MAM	Filler	Talc, surface treated	HOFFMANN MINERAL
Styrenated phenol	Antioxidant		several
Sulfur	Curing agent		several
Supercarborex	Filler	Whiting	Omya
TAC	Co-agent for peroxide cure	Triallyl-cyanurate	several
TAC /GR 50	Co-agent for peroxide cure	Triallyl-cyanurate, granules 50 %	Kettlitz-Chemie
TAC /GR 70	Co-agent for peroxide cure	Triallyl-cyanurate, granules 70 %	Kettlitz-Chemie




Product	Function	Description	Supplier
Tackirol 201	Crosslinking resin	Alkylphenol-formaldehyde resin	Taoka Chemical
TAIC	Co-agent for peroxide cure	Triallyl isocyanurate	several
TDEC	Accelerator	Tellurium-diethyl-dithiocarbamate	several
TDEC Gran 75	Accelerator	Tellurium-diethyl-dithiocarbamate, 75 % polymer bound	several
TEA	Filler activator	Triethanol amine	several
Tecnoflon FOR M1	Crosslinking batch	Based on bisphenol A/F	Solvay Solexis
Tecnoflon FOR M2	Accelerator batch	Phosphonium salt	Solvay Solexis
Tecnoflon T 636	Polymer	FKM	Solvay Solexis
TESPT	Coupling agent	Bis (triethoxysilylpropyl) tetrasulfide	several
TETD	Accelerator	Tetraethyl-thiuram-disulfide	several
Tetrone A	Accelerator	Dipentamethylene-thiuram-hexa-sulfide	DuPont
Therban 3407	Polymer	HNBR	Arlanxeo
Therban 3607	Polymer	HNBR	Arlanxeo
Tin(II) chloride dihydrate crystalline	Activator		several
Tinuvin 123	Light stabilizer	Liquid HALS stabilizer based on amino ether	BASF
Tinuvin 622 LD	Antioxidant	Sterically hindered amine	BASF
Titanium dioxide	White pigment		several
Titanium dioxide rutile	White pigment	Rutile type	several
Titanium dioxide R-KB-2	White pigment	Rutile type	several
TMPT	Co-agent for peroxide cure	Trimethylol-propane-trimethacrylate	several
TMQ	Antioxidant	2,2,4-trimethyl-1,2-dihydro-quinoline	several
TMTD	Accelerator	Tetramethyl-thiuram-disulfide	several
TMTM	Accelerator	Tetramethyl-thiuram-monosulfide	several
TP 2005087	Filler	Neuburg Siliceous Earth, surface treated	HOFFMANN MINERAL
TRACEL K 3/95	Blowing agent	Modified azodicarbonamide, oil-treated	Tramaco
TRACEL OBSH 75 EPR-1	Blowing agent	Oxy-bis (benzenesulfonyl hydrazide) (OBSH), predispersed in EPDM	Tramaco




Product	Function	Description	Supplier
Trigonox 101	Curing agent	2,5-dimethyl-2,5-di (tert-butyl-peroxy) hexane	Nouryon
Trigonox 101-50D	Curing agent	2,5-dimethyl-2,5-di (tert-butyl-peroxy) hexane, 50 %	Nouryon
Trigonox 29-40	Curing agent	1,1-di-t-butylperoxy-3,3,5-trimethyl-cyclohexane, 40 %	Nouryon
Trigonox 29-40B	Curing agent	1,1-di-t-butylperoxy-3,3,5-trimethyl-cyclohexane 40 % bound to whiting and silica	Nouryon
Trigonox C-50D	Curing agent	Tert-butyl-peroxy-benzoate, 50 % bound to silica	Nouryon
TRIM	Co-agent for peroxide cure	trimethylol-propane-trimethacrylate (TMPT)	several
Tronox R-UF	White pigment	Titanium dioxide No longer available. Recommended: Crenox R-U-5.	
Tudalen B 8014 Extra	Plasticizer	Paraffin oil	H & R Group (Dahleke)
Ultrasil VN 2	Filler	Precipitated silica, 130 m <sup>2</sup> /g	Evonik Industries
Ultrasil VN 3	Filler	Precipitated silica, 170 m <sup>2</sup> /g	Evonik Industries
Vamac D	Polymer	AEM No longer available. Recommended: Vamac DP	
Vamac DP	Polymer	AEM	DuPont
Vamac G	Polymer	AEM	DuPont
Vamac G1	Polymer	AEM No longer available. Recommended: Vamac G	
Vamac Ultra IP	Polymer	AEM	DuPont
Vanfre VAM	Processing aid	Polyoxyethylene octadecyl ether phosphate	Vanderbilt
Vanox ZMTI	Antioxidant	Zinc-mercapto-tolu-imidazole	Vanderbilt
Varox DBPH-50	Curing agent	2,5-dimethyl-2,5-di (tert.-butyl-peroxy) hexane	Vanderbilt
Vaseline	Processing aid		several
Vestolen A 3512	Processing aid	High density polyethylene, MFR 0,5 g/10 min No longer available. Recommended: SABIC LLDPE 0132HS00	
Vistalon 404	Polymer	EPDM	ExxonMobil Chemical



Product	Function	Description	Supplier
Vistalon 2504	Polymer	EPDM	ExxonMobil Chemical
Vistalon 3666	Polymer	EPDM, oil extended	ExxonMobil Chemical
Vistalon 5601	Polymer	EPDM	ExxonMobil Chemical
Vistalon 5630	Polymer	EPDM, oil extended No longer available. Recommended: Vistalon 5601 + 30 phr plasticizer oil	
Vistalon 6505	Polymer	EPDM	ExxonMobil Chemical
Vistalon 6630	Polymer	EPDM, oil extended No longer available. Recommended: Vistalon 8700 + 30 phr plasticizer oil	
Vistalon 7001	Polymer	EPDM	ExxonMobil Chemical
Vistalon 7500	Polymer	EPDM	ExxonMobil Chemical
Vistalon 7606	Polymer	EPDM No longer available. Recommended: Vistalon 7001	
Vistalon 7700	Polymer	EPDM	ExxonMobil Chemical
Vistalon 8510	Polymer	EPDM, oil extended No longer available. Recommended: Vistalon 8800	
Vistalon 8600	Polymer	EPDM	ExxonMobil Chemical
Vistalon 8700	Polymer	EPDM	ExxonMobil Chemical
Vistalon 8800	Polymer	EPDM, oil extended	ExxonMobil Chemical
Vistalon 9500	Polymer	EPDM	ExxonMobil Chemical
Viton GAL-200S	Polymer	FKM	Chemours
Viton A-201C	Polymer	FKM	Chemours
Vulcofac F45	Aktivator	Calciumhydroxid	Safic-Alcan
Vulcofac HDC	Aktivator	Hexamethylene diamine carbamate	Safic-Alcan
Vulkacit 576	Accelerator	Condensation product of butyraldehyde und aniline	Lanxess
Vulkacit CZ	Accelerator	Cyclohexyl-benzothiazyl-sulfenamide (CBS)	Lanxess
Vulkacit D	Accelerator	Diphenyl-guanidine	Lanxess
Vulkacit DM	Accelerator	Dibenzo-thiazyl-disulfide (MBTS)	Lanxess
Vulkacit DM/C	Accelerator	Dibenzo-thiazyl-disulfide (MBTS)	Lanxess
Vulkacit DZ/EG-C	Accelerator	N,N-dicyclohexyl-2-benzothiazyl sulfenamide (DCBS)	Lanxess



Product	Function	Description	Supplier
Vulkacit I	Accelerator	Dimethyl-diphenyl-thiuram-disulfide	Lanxess
Vulkacit LDA	Accelerator	Zinc-diethyl-dithiocarbamate (ZDEC)	Lanxess
Vulkacit Mercapto	Accelerator	Mercapto-benzothiazole (MBT)	Lanxess
Vulkacit MOZ	Accelerator	Benzothiazyl-sulfenmorpholide (MBS)	Lanxess
Vulkacit P extra N	Accelerator	Zinc-ethylphenyl-dithiocarbamate (ZEPC)	Lanxess
Vulkacit Thiuram	Accelerator	Tetramethyl-thiuram-disulfide (TMTD)	Lanxess
Vulkalent B/C	Cure retarder	Phthalic anhydride	Rhein Chemie
Vulkalent E/C	Cure retarder	Sulfonamide derivate	Rhein Chemie
Vulkanol 81	Plasticizer	Blend of thioesters and carboxylic acid esters	Rhein Chemie
Vulkanol FH	Plasticizer	Aromatic polyether	Rhein Chemie
Vulkanol OT	Plasticizer	Ether-thioether	Rhein Chemie
Vulkanox 4010 NA	Antioxidant	Isopropyl-phenyl-p-phenylene-diamine (IPPD)	Lanxess
Vulkanox 4020	Antioxidant	1,3-dimethylbutyl-phenyl-p-phenylene diamine (6PPD)	Lanxess
Vulkanox BKF	Antioxidant	2,2'-methylene-bis-(4-methyl-6-tert-butylphenol) (BPH)	Rhein Chemie
Vulkanox HS	Antioxidant	2,2,4-trimethyl-1,2-dihydro-quinoline (TMQ), polymerized	Lanxess
Vulkanox KSM	Antioxidant	Alkylated phenol No longer available. Recommended: Vulkanox SP	
Vulkanox MB	Antioxidant	Mercapto-benzimidazole (MBI)	Lanxess
Vulkanox MB/MG	Antioxidant	Mercapto-benzimidazole (MBI), microgranules	Lanxess
Vulkanox SP	Antioxidant	Styrenated phenol	Lanxess
Vulkanox ZMB2	Antioxidant	Zinc-methyl-mercapto-benzimidazole (ZMMBI)	Lanxess
Vulkanox ZMB2/C-5	Antioxidant	Zinc-4- and 5-methyl-2-mercapto-benzimidazole (ZMMBI)	Lanxess
Vulkasil A1	Filler	Sodium aluminosilicate, 50-80 m <sup>2</sup> /g	Rhein Chemie
Vulkasil N	Filler	Precipitated silica, 130 m <sup>2</sup> /g	Rhein Chemie
Vulkasil S	Filler	Precipitated silica, 175 m <sup>2</sup> /g	Rhein Chemie



Product	Function	Description	Supplier
Wax	Processing aid		several
Weichmacher 450	Plasticizer	Aromatic oil	Fuchs Europe Schmierstoffe
Whiting	Filler		several
Winnofil S	Filler	Precipitated calcium carbonate, surface treated	Solvay
Wollastonite	Filler		several
X_Butyl RB 301	Polymer	IIR	Arlanxeo
Z5MC	Accelerator	Zinc-pentamethylene-dithiocarbamate	several
ZBEC	Accelerator	Zinc-dibenzyl-dithiocarbamate	several
ZBPD	Accelerator	Zinc-dibutyl-dithiophosphate	several
ZDBC	Accelerator	Zinc-dibutyl-dithiocarbamate	several
ZDEC	Accelerator	Zinc-diethyl-dithiocarbamate	several
ZDMC	Accelerator	Zinc-dimethyl-dithiocarbamate	several
ZEPC	Accelerator	Zinc-ethylphenyl-dithiocarbamate	several
Zetpol 1010	Polymer	HNBR, 44 % ACN	Zeon Europe
Zinc oxide	Activator		several
Zinc oxide RS	Activator	Zinc oxide	several
Zinkoxyd aktiv	Activator	Zinc oxide	Rhein Chemie
Zinc White Harzsiegel	Activator	Zinc oxide	Norzinco
Zinc stearate	Processing aid, activator		several
ZIX	Accelerator	Zinc-isopropyl-xanthogenate	several

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.