



2K Epoxy industrial flooring self-leveling, water-borne

Basis Epoxy resin (bisphenol A / epichlorohydrin and tertiary amine)

	Guide Formulation of Byk Chemie	RRS 2172
Component A	Epikure 8545-W-52	(1) 11.6
	Epikure 3253	(1) 0.3
	Water	11.6
	Disperbyk-194 N	(2) 2.2
	Byk-1711	(2) 2.0
	Rheobyk-420	(2) 1.0
	SILLITIN Z 89	(3) 15.9
	Blanc Fixe micro	(4) 26.5
	Millisil W 8	(5) 5.3
	Millisil W 10	(5) 5.3
	Tioxide TR 92	(6) 10.8
	Water	7.7
Total parts by weight component A		100.2

Component B Epikote Resin 816 MV (1) 7.5

Mixing ratio A:B 100 : 7.5 parts by weight

Note After grinding adjust viscosity with 2.5 % water onto component A.

Suppliers

- (1) Hexion
- (2) Byk Chemie
- (3) HOFFMANN MINERAL
- (4) Venator Materials Corporation
- (5) Quarzwerke
- (6) Huntsman Pigments

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.