



**Facade paint, water-based, white, matte
reduced dirt pick-up**

Basis	Acrylic dispersion				
	Base formulation FP 2019/1 of Alberdingk Boley				
Mill base	Water			9.25	
	Orotan 731	(1)		1.30	
	Tego Foamex 810	(2)		0.10	
	Aquaflow NLS-205	(3)		0.40	
	Kronos 2190	(4)		23.00	
	Hydrocarb OG	(5)		5.60	
	SILLITIN Z 89)*	(6)		3.40	
	Tego Airex 902 W	(2)		0.10	
Let down stage	Water			15.50	
	Dowanol DPnP	(1)		1.00	
	Alberdingk AC 2019 VP	(7)		31.70	
	Aquaflow NLS-205	(3)		1.80	
	Total parts by weight			93.15	
	Guide formulation of Nouryon (ex AkzoNobel)				
Completion	Base formulation FP 2019/1		A	B	C
	Levasil CC301	(8)	90	85	75
	Total parts by weight		100	100	100

)* or SILFIT Z 91: lower yellowish tint

Suppliers	(1)	Dow Chemical Company
	(2)	Evonik Tego Chemie
	(3)	Ashland
	(4)	Kronos International
	(5)	Omya
	(6)	HOFFMANN MINERAL
	(7)	Alberdingk Boley
	(8)	Nouryon



		A	B	C
Technical Data	<u>Dirt pick-up as total color change ΔE</u>			
	Iron oxide, rinsed with water	1.25	0.55	0.25
	Iron oxide, rinsed with soaped water	0.26	0.17	0.12
	Carbon black, rinsed with water	2.79	2.93	1.43
	Carbon black, rinsed with soaped water	1.23	0.71	0.43
Spreading rate	m ² /l	9.1	9.6	9.8

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.