



## CONSTRUCTION INDUSTRY

### Roof sheet, black

#### 70 Shore A, EPDM, thermoplastic

Guide formulation of Hüls (now Evonik)		3116 B2
Buna AP 447 )*		100
Zinc oxide RS		5
Stearic acid		2
Process Oil P 100 (ex Sunpar 150)		40
Atactic polybutene		40
Corax N 550		70
SILLITIN Z 86		220
Aflux 42		5
Total phr		482
Density	g/cm <sup>3</sup>	1.45

)\* No longer available. Recommended: Keltan 5470 or Keltan 5470Q

#### Physical properties

Hardness	Shore A	approx. 70
Tensile strength	MPa	approx. 4,5
Elongation at break	%	approx. 230

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.