



ELECTRICAL APPLICATON
Sheathing, light-colored

60 Shore A, EPDM, peroxide cure

Guide formulation of Hüls (now Evonik)	3386 K460
Buna AP 258)*	130.0
Zinc oxide RS	4.0
Stearic acid	1.0
SILLITIN Z 86	150.0
Vulkasil N	30.0
Paraffin oil	25.0
Rhenofit TAC/S	1.1
Polydispersion E (VC) D-40	6.0
Total phr	347.1

)* No longer available. Recommended: Keltan 3973

Physical properties

Hardness	Shore A	approx. 60
Tensile strength	MPa	approx. 10
Elongation at break	%	approx. 750

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.