



CONSTRUCTION INDUSTRY

Flooring, light-colored

Building flooring

75 Shore A, EPDM, sulfur cure / compression molding

Specification DIN 16852

Guide formulation of Exxon		861 B 41001
Vistalon 7001		70.0
Vistalon 2504		30.0
Perkasil KS 300		40.0
Titanium dioxide		15.0
SILLITIN P 87		150.0
Paraffin oil		45.0
Paraffin wax		5.0
PEG 3350		3.0
Struktol WB 212		2.0
Polyethylene wax		5.0
Silquest A-189		1.0
Stearic acid		2.0
Zinc oxide		5.0
Sulfur		1.5
MBT		1.5
TMTD		1.5
ZDMC		1.5
ZDBC		1.5
Total phr		380.5
Density	g/cm ³	1.38
Mooney Viscosity		
ML (1+4) 100°C	MU	60
ODR, ± 3°, 180°C		
ML, minimum	dNm	10
MH, maximum	dNm	67
ts ₂	min	1.4
tC ₉₀	min	9.0



861 B 41001

Physical properties**Press cure 12 min @ 180°C**

			DIN 16852	
Hardness		Shore A	73	> 70
Modulus 100 %		MPa	2.7	
Tensile strength		MPa	9.5	
Elongation at break		%	450	
Abrasion, 5 N	DIN ISO 4649	mm ³	130	< 150

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.