


## CONSTRUCTION INDUSTRY

### Profile, solid, light-colored

#### Building profile

75 Shore A, EPDM, sulfur cure / LCM cure

Guide formulation of Exxon		871 E 237
Vistalon 7500		100.0
Titanium dioxide		15.0
SILLIKOLLOID P 87		280.0
Grundöl AP/E Core 600 (ex Flexon 876)		55.0
PEG 3350		3.0
Benzoic acid		2.0
Kagevest 25 (ex Polyvest 25)		2.0
Stearic acid		2.0
Zinc oxide		8.0
Calcium oxide		10.0
Sulfur		0.5
MBT		1.0
TMTD		2.5
ZDEC		1.5
ZDBC		1.5
DTDM		2.0
Total phr		486.0
Density	g/cm <sup>3</sup>	1.57
<b>Mooney Viscosity</b>		
ML (1+4) 100°C	MU	76
<b>ODR, ± 3°, 180°C</b>		
ML, minimum	dNm	8
MH, maximum	dNm	78
ts <sub>2</sub>	min	1.3
tc <sub>90</sub>	min	4.2

**Physical properties****Press cure 5 min @ 180°C**

Hardness	Shore A	73
Modulus 100 %	MPa	4.2
Tensile strength	MPa	5.9
Elongation at break	%	340

**Compression set****Press cure 8 min @ 180°C**

22 h @ -25°C, 25 % defl.	ASTM B	%	43
22 h @ 70°C, 25 % defl.	ASTM B	%	15
22 h @ 100°C, 25 % defl.	ASTM B	%	29

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.