



CONSTRUCTION INDUSTRY


Profile, solid, black

Building profile

80 Shore A, EPDM, sulfur cure / CV cure

Specification AFNOR 85301

Guide formulation of Exxon		891 E 302
Vistalon 7500		100.0
FEF N-550		160.0
SILLITIN P 87		50.0
Grundöl AP/E Core 600 (ex Flexon 876)		90.0
Kagevest 25 (ex Polyvest 25)		2.0
Stearic acid		1.0
Zinc oxide		5.0
Calcium oxide		10.0
Sulfur		0.5
TMTD		2.0
ZDMC		1.5
ZDEC		1.5
DTDM		2.0
Total phr		425.5
Density	g/cm ³	1.25
Mooney Viscosity		
ML (1+4) 100°C	MU	68
ODR, ± 3°, 180°C		
ML, minimum	dNm	11
MH, maximum	dNm	65
ts ₂	min	1.3
tc ₉₀	min	3.2
Physical properties		
Press cure 5 min @ 180°C		
Hardness	Shore A	78
Modulus 100 %	MPa	6.8
Tensile strength	MPa	10.4
Elongation at break	%	175



891 E 302

				AFNOR
				85301
Compression set				
Press cure 8 min @ 180°C				
22 h @ 100°C, 25 % defl.	ASTM B	%	25	< 25
Tension set				
7 d @ 100°C, 20 % elongation		%	56	< 90
Elastic recovery				
22 h @ -25°C, 25 % deflection		%	30	> 10
Air aging, 14 d @ 100°C				
Δ Hardness		Shore A	+7	± 10
Δ Tensile strength		%	-3	± 15
Δ Elongation at break		%, rel.	-28	< 30
Elongation at break		%	110	> 80
Δ Weight		%	-0.9	< 3

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.