


CONSTRUCTION INDUSTRY

Profile, solid, black

Building profile, flame retardant halogen free

60 Shore A, EPDM, peroxide cure / steam cure

Guide formulation of Exxon		921 Y 001
Vistalon 7500		50
Vistalon 2504		50
Polyethylene wax		5
FEF N-550		30
SILLITIN P 87		40
Martinal OL-111 LE		140
Grundöl AP/E Core 2500 (ex Flexon 815)		50
Kagevest 25 (ex Polyvest 25)		2
Struktol WB 212		3
TMQ		1
Vanox ZMTI		2
EDMA		1
Antilux 500 L		2
Perkadox 14-40		8
Total phr		384
Density	g/cm ³	1.35
Mooney Viscosity		
ML (1+4) 100°C	MU	39
ODR, ± 3°, 180°C		
ML, minimum	dNm	5
MH, maximum	dNm	49
ts ₂	min	1.0
tC ₉₀	min	7.9



921 Y 001

Physical properties**Press cure 10 min @ 180°C**

Hardness	Shore A	62
Modulus 100 %	MPa	2.4
Tensile strength	MPa	8.6
Elongation at break	%	400

Compression set**Press cure 12 min @ 180°C**

22 h @ 70°C, 25 % deflection	%	19
22 h @ 100°C, 25 % deflection	%	13

LOI	%	27
------------	---	----

Air aging, 7 d @ 100°C

Δ Hardness	Shore A	+4
Δ Tensile strength	%	+4
Δ Elongation at break	%, rel.	-12

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.