



CONSTRUCTION INDUSTRY

Profile, solid, light-colored


Building profile

55 Shore A, EPDM, sulfur cure / LCM or hot air cure

Guide formulation of Exxon		A.1.3.002
Vistalon 6630)*		130.0
SILLITIN P 87		220.0
Paraffin oil		70.0
PEG 3350		10.0
Titanium dioxide		10.0
Zinc oxide		10.0
Stearic acid		1.0
Silquest A-189		1.0
Calcium oxide 80 %		10.0
Sulfur		1.5
MBT		1.0
ZDMC		4.0
TDEC		1.0
Total phr		469.5
Density	g/cm ³	1.35

)* No longer available. Recommended: 100 phr Vistalon 8700 + 30 phr plasticizer

Monsanto Rheometer, $\pm 5^\circ$		120°C	200°C
ML, minimum	dNm	11.5	7.0
MH, maximum	dNm	---	46
ts ₂	min	2.4	0.4
tc ₉₀	min	---	1.7



A.1.3.002

		Press	Hot air
		2 min @ 200°C	
Physical properties			
Hardness	Shore A	55	53
Modulus 100 %	MPa	1.5	1.5
Modulus 300 %	MPa	3.2	3.0
Tensile strength	MPa	6.0	6.2
Elongation at break	%	570	680
Tension set, hot air cured profile			
22 h @ 70°C, 100 % elongation, 30 min cooling under tension / 48 h relaxation		---	22.5
Compression set			
22 h @ 70°C	ASTM B	3 min @ 200°C 35	---

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.