



CONSTRUCTION INDUSTRY
Profile, sponge, light-colored

Density 0.40 g/cm³, EPDM, sulfur cure / LCM cure

Guide formulation of Exxon	RRS 3
Vistalon 8510)*	115.00
SILLITIN Z 86	100.00
Grundöl AP/E Core 600 (ex Flexon 876)	70.00
Zinc oxide	8.00
Stearic acid	1.00
PEG 3350	3.00
Silquest A-189	1.50
Rhenogran CaO-80	2.25
Sulfur	1.50
MBT	1.50
TMTD	0.80
DPTT	1.00
ZDBC	1.50
TDEC	0.80
Genitron ACR	2.00
Blowing agent BSH	1.00
Porofor TSH	1.00
Total phr	311.85

)* No longer available. Recommended: Vistalon 8800


ODR		120°C
ML, minimum	dNm	11
t ₅	min	2.2

ODR		180°C
ML, minimum	dNm	10
MH, maximum	dNm	61
ts ₂	min	0.4
tC ₉₀	min	2.6

Physical properties

LCM cure @ 245°C

Density	g/cm ³	0.4
Load deflection, 50 % deflection	N/cm	16



RRS 3

Compression set

22 h @ RT, 25 % deflection	%	22
22 h @ 40°C, 25 % deflection	%	40

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.