



CONSTRUCTION INDUSTRY

Flooring, light-colored

80 Shore A, EPDM, sulfur cure

Guide formulations of Degussa (now Evonik)	RRS 10	RRS 11
Keltan 578Z)*	100.0	100.0
SILLIKOLLOID P 87	150.0	150.0
Ultrasil VN 2	40.0	---
Coupsil 6411	---	44.0
Zinc oxide RS	5.0	5.0
Stearic acid	2.0	2.0
Titanium dioxide	15.0	15.0
Paraffin oil	45.0	45.0
Protektor G 35 P	5.0	5.0
Struktol WB 212	2.0	2.0
PEG 4000	3.0	3.0
MBT	1.5	1.5
TMTD	1.5	---
ZDMC	1.5	---
ZDEC	1.5	---
ZBEC	---	3.0
Sulfur	1.5	1.5
Total phr	374.5	377.0

)* No longer available. Recommended: Keltan 5470 or Keltan 5470Q

Mooney Viscosity

ML (1+4) 100°C	DIN 53523	MU	72	62
----------------	-----------	----	----	----

Rheometer, 180°C

M _{HF} - M _L		Nm	10.30	9.66
M _L		Nm	1.58	1.09
t _{10%}		min	2.1	2.5
t _{90%}		min	4.8	6.2
t _{90%} - t _{10%}		min	2.7	3.7



			RRS 10	RRS 11
Physical properties				
Cure @ 180°C				
			10 min	13 min
Hardness	DIN ISO 7619-1	Shore A	76	81
Modulus 300 %		MPa	3.9	7.9
Tensile strength	DIN 53504, RI	MPa	8.0	8.2
Elongation at break		%	510	330
Rebound	DIN 53512	%	50	51
Abrasion	DIN ISO 4649	mm ³	445	320
Compression set				
22 h @ 70°C	ASTM D 395 B	%	25.2	18.6

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.