



## MACHINERY and EQUIPMENT

### Roller cover, light-colored

20 Shore A, PNR, sulfur cure

Guide formulation of Astrotech Advanced Elastomerproduct (original: Nippon Zeon)	RRS 17
Norsorex 150 NA	250.0
Naphthenic oil	100.0
Whiting	100.0
SILLITIN Z 86	50.0
Titanium dioxide	10.0
Zinc oxide	5.0
Stearic acid	1.0
TMTD	1.5
DTDM	1.5
Vulkacit I	1.5
Ethyl Tellurac	0.8
DOTG	1.0
ETU	0.5
Total phr	522.8

ODR Monsanto		160°C	180°C
ts <sub>2</sub>	min	6.5	2.8
tc <sub>100</sub>	min	20	6.0

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.