



## MACHINERY and EQUIPMENT

### Appliance, Gasket, light-colored

#### Washing machine gasket

##### 45 Shore A, EPDM, sulfur cure

Guide formulation of Exxon	RRS 18
Vistalon 7001	50.0
Vistalon 7500	50.0
SILLIKOLLOID P 87	145.0
Titanium dioxide	10.0
Grundöl AP/E Core 600 (ex Flexon 876)	95.0
Zinc oxide	5.0
Stearic acid	1.0
PEG 3350	2.0
Kagevest 25 (ex Polyvest 25)	2.0
TMQ	0.5
Sulfur	0.5
MBTS	1.5
DPTT	1.0
Rhenogran ZAT-70	1.0
Total phr	364.5

#### Mooney Viscosity

ML (1+4) 100°C	MU	20
----------------	----	----

#### ODR, ± 3°, 180°C

ML, minimum	dNm	2
MH, maximum	dNm	37
ts <sub>2</sub>	min	2.1
tC <sub>90</sub>	min	4.2

#### Physical properties

##### Press cure @ 180°C

Hardness	Shore A	47/43
Modulus 100 %	MPa	1.1
Tensile strength	MPa	8.0
Elongation at break	%	> 775

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.