



## MACHINERY and EQUIPMENT

### Roller cover, light-colored

### Paper press with high heat conductivity

90 Shore A, NR, sulfur cure

Guide formulation of Dr. Zeppernick, GAK 12/1993 Dr. Gupta Verlag	RRS 27
NR	100.0
Paraffin wax	1.0
Magnesium oxide	4.0
Antioxidant PBN	1.3
Antioxidant MB	0.7
Antioxidant HS	1.0
Sterically hindered phenol	1.4
SILLITIN Z 86	190.0
Vulkacit CT/N )*	0.7
CTP (PVI)	0.8
Sulfur	14.0
Total phr	314.9

)\* No longer available. Recommended: Vulkacit 576

### Physical properties

Hardness Shore A 93  
good resistance to toluene

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.