



MACHINERY and EQUIPMENT

Roller cover, light-colored

Replacement for stone rollers with high heat conductivity

40 Shore D, SBR / NR, sulfur cure

Guide formulation of Dr. Zeppernick, GAK 12/1993 Dr. Gupta Verlag	RRS 28
NR	30.0
SBR	70.0
Paraffin wax	0.6
Resin	17.0
Magnesium oxide	15.0
Zinc oxide	50.0
SILLITIN N 85	50.0
Quartz sand	200.0
Titanium dioxide	24.0
Sulfur	27.0
Total phr	483.6

Physical properties

Hardness	Shore D	40
----------	---------	----

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.