



ELECTRICAL APPLICATION

Terminator cable, light-colored

50 Shore A, EPDM, sulfur cure

Guide formulation of EniChem (now Polimeri Europa)	RRS 29
Dutral TER 6235	125.0
Zinc oxide	10.0
Stearic acid	1.0
PEG 4000	10.0
SILLIKOLLOID P 87	220.0
Titanium dioxide	10.0
Cortis 100 M	75.0
Silquest A-189	1.0
MBT	0.9
ZDMC	3.6
TDEC	0.9
Sulfur	1.3
Caloxol W3	5.0
Total phr	463.7

ODR Monsanto, 180°C

ts ₂	min	0.9
tc ₉₀	min	3.5

Physical properties

Cure 20 min @ 160°C

Hardness	Shore A	52
Modulus 300 %	MPa	2.5
Tensile strength	MPa	6.5
Elongation at break	%	660

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.