



## AUTOMOTIVE INDUSTRY

### Profile, sponge, black

#### Smooth skin, excellent load deflection

Density 0.50 g/cm<sup>3</sup>, EPDM, sulfur cure / UHF cure

Guide formulation of DSM (now Arlanxeo)	S 8943
Keltan 8340A )*	100.00
Zinkoxyd aktiv	5.00
Stearic acid	1.00
Polyethylene glycol	2.00
Calcium oxide 80 %	2.14
Spheron 5000	70.00
SILLITIN N 85	35.00
Paraffin oil	70.00
MBT 80 %	2.00
ZBEC 70 %	2.50
ZBPD 50 %	2.50
Rhenogran S-80	1.90
OBSH	3.00
ZIX	1.00
Total phr	298.04

)\* No longer available. Recommended: Keltan 8550C

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.