



AUTOMOTIVE INDUSTRY

Molding, light-colored

AKTIFIT AM in combination with silica in AEM

70/80 Shore A, AEM, diamine cure

	Ultrasil VN 2 AKTIFIT AM	60 phr ---	30 phr 60 phr	20 phr 80 phr
Guide formulations of DuPont	AEM	9913	9914	9919
Vamac Ultra IP		100.0	100.0	100.0
Naugard 445		2.0	2.0	2.0
Armeen 18D Prills		0.5	0.5	0.5
Ofalub SEO		1.5	1.5	1.5
Stearic acid		1.0	1.0	1.0
Ultrasil VN 2		60.0	30.0	20.0
Dynasylan AMEO		1.0	0.5	0.5
AKTIFIT AM		---	60,0	80.0
Alcanplast PO 80		10.0	10.0	10.0
Vulcofac HDC		1.3	1.3	1.3
Alcanpoudre DBU-70		3.0	3.0	3.0
Total phr		180.3	209.8	219.8

Combining silica with AKTIFIT AM results in

- improved processing due to reduced viscosity
(see viscosity ML 1+4 @ 120°C and MDR min. torque @ 180°C)
- shorter conversion time
- markedly improved compression set
- slightly improved heat resistance



Ultrasil VN 2	60 phr	30 phr	20 phr
AKTIFIT AM	---	60 phr	80 phr
AEM	9913	9914	9919

Rheological properties

Mooney Viscosity ML (1+4) @ 120°C	MU	88	53	52
MDR Min. Torque @ 180°C	dNm	2.43	0.55	0.46
MDR Max. Torque @ 180°C	dNm	31.67	17.40	16.44
MDR Cure Rate @ 180°C	dNm/min	10	7.2	7.0
MDR t ₁₀ @ 180°C	min	0.71	0.78	0.74
MDR t ₉₀ @ 180°C	min	8.8	7.7	6.9

Mechanical properties

Cure 10 min @ 180°C + post cure 4 h @ 175°C

Hardness	DIN ISO 7619-1	Shore A	81	71	68
Tensile strength		MPa	16	16	15
Modulus 50 %		MPa	2.6	2.4	2.3
Modulus 100 %		MPa	4.7	6.5	6.9
Elongation at break		%	279	209	185
Tear resistance (Type C, Crescent)		kN/m	27	19	18
Tear resistance (Type A, Trouser)		kN/m	9.4	3.5	2.8
Compression set					
70 h @ 150°C, 25 % deflection	DIN ISO 815-1	%	37	17	14
1008 h @ 150°C, 25 % deflection	DIN ISO 815-1	%	58	40	39
94 h @ 150°C, 50 % deflection, 5s	VW PV 3307	%	58	41	36

Air aging, 1008 h @ 150°C, post cured specimen

Hardness		Shore A	83	73	69
Tensile strength		MPa	15	15	14
Modulus 100 %		MPa	6.0	7.0	6.8
Elongation at break		%	215	202	190
Δ Hardness		Shore A	+2	+2	+1
Δ Tensile strength		%	-10	-5	-7
Δ Modulus 100 %		%	+26	+7	-1
Δ Elongation at break		%, rel.	-23	-3	+3

Mechanical properties @ 150°C

Tensile strength		MPa	5.1	5.3	4.6
Modulus 50 %		MPa	2.3	2.5	2.5
Elongation at break		%	117	88	76
Tear resistance (Type C, Crescent)		kN/m	9.0	4.4	3.7

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.