



Industrial coating

UV-curing soft feel lacquer for wood

Basis Urethane acrylate

Guide Formulation of Bayer Polymers (06/2003)		FWO 4460-30
Ebecryl 4491	(1)	20.0
Ebecryl 4101	(1)	20.0
Syloid ED 30	(2)	8.0
SILLITIN V 88	(3)	8.0
TPGDA	(1)	40.0
Omnirad 1173	(4)	4.0
Total % by weight		100.0

Technical Data Viscosity (23°C) approx. 5000 mPa-s

Suppliers

- (1) Allnex
- (2) Grace
- (3) HOFFMANN MINERAL
- (4) IGM Resins

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.