



2K-Polyaspartic floor coat
Flex Coat, self-leveling, solvent-free
60 Shore D

Basis Polyaspartic (polyaspartic ester / isocyanate HDI)

	Guide Formulation of Covestro		WKHB 512/2
Component A	Desmophen NH 1420	(1)	21.5
	Desmophen NH 1720	(1)	9.2
	Sylosiv A4	(2)	0.7
	Tego Airex 944	(3)	0.4
	Tego Wet 250	(3)	0.1
	SILLITIN Z 86	(4)	26.7
	Colortherm Green GN	(5)	4.7
Component B	Desmodur E 2863 XP	(1)	27.5
	Desmodur ultra N 3900	(1)	9.2
	Total % by weight		100.0

Recommendation For better dispersibility and mechanical properties SILLITIN Z 86 PURISS is recommended.
 For brighter applications SILLITIN Z 89 / SILLITIN Z 89 PURISS are suitable.

Mixing Preparing component A under vacuum (approx. 200 mbar) has been proved ideal regarding the incorporation of air and to achieve the mentioned working time.
 Allow component A to age for at least 24 h prior to use.

Processing Premix the two Desmodur types prior to use.
 Mix component A and B properly prior to the application.
 The tough coat can be applied by trowel.

Suppliers

- (1) Covestro
- (2) Grace
- (3) Evonik Tego Chemie
- (4) HOFFMANN MINERAL
- (5) Lanxess



WKHB 512/2

Composition			
	Binding agent	% (w/w)	approx. 67.4
	Additives	% (w/w)	approx. 1.2
	Pigments and fillers	% (w/w)	approx. 31.4
	Calculated solvent content	% (w/w)	0
Technical Data			
	Mixing ratio A : B (% by weight)		approx. 64 : 36
	Crosslinking ratio NCO : OH	%	approx. 110
	Working time (manual)	min	approx. 35
	Drying time, 400 µm wet, drying recorder	min	approx. 150 /
	Hardness, after 3d @ 50°C	Shore A / D	approx. 85 / 59
	Pendulum hardness Koenig, after 7 / 56d @ RT	s	approx. 35 / 71
	Abrasion loss CS 17 (10 N, 1000 cycles)	mg	approx. 36.6
	Glass transition temperature T _g	°C	approx. 27.5
	Tensile strength, after 3d @ 50°C	N/mm ²	approx. 64
	Elongation at break, after 3d @ 50°C	%	approx. 91
	Tear resistance, after 3d @ 50°C	N/mm	approx. 14

The tests were done @ 23°C / 50 % RH.

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.