



Interior dispersion paint
dull matte, highly wet-scrub resistant, good opacity
easy-to-clean, cost-effective

Basis Dispersion based on vinyl acetate/ethylene/acrylate

Guide Formulation of Wacker Chemie			LA006MM31A
Water			240
Benaqua 4000	(1)		3
Agitan 281	(2)		4
Coadis 234 K	(3)		4
AMP-90	(4)		2
Kronos 2300	(5)		187
AKTISIL MAM	(6)		162
AKTIFIT Q	(6)		5
Vinnapas EAF 380	(7)		366
Coapur XS 71, 25 % in water	(3)		10
Silres BS 168	(7)		3
Texanol	(8)		15
Total parts by weight			1001

Properties	PVC	%	approx. 40
Gloss 60°	DIN EN ISO 2813	GU	3
Gloss 85°	DIN EN ISO 2813	GU	5 (dull matte)
Wet-scrub resistance	DIN EN ISO 11998	µm	3 (class 1)
Hiding power at 8 m ² /l	DIN ISO 6504-3	%	98.1 (class 2)
Household stains			coffee, lipstick, highlighter, pencil

Suppliers	(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)
	Elementis	Münzing Chemie	Coatex (Arkema)	Advancion	Kronos International	HOFFMANN MINERAL	Wacker Chemie	Eastman Chemical Company

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.