



AUTOMOTIVE INDUSTRY
Car polish, with solvents
conventional

		RR 002
Licowax LP	(1)	2.5
Licowax E	(1)	1.0
Emulsogen OG	(1)	1.5
Exxsol D 145/160	(2)	36.5
Wacker AK 350	(3)	2.0
Wacker AK 12500	(3)	2.0
Water, softened		41.5
SILLITIN N 85 PURISS	(4)	13.0
Preservative		as needed
Total % by weight		100.0

- Mixing**
- heat Exxsol D 145/160, Licowax LP, Licowax E, Emulsogen OG, Wacker AK 350 and Wacker AK 12500 to 95 °C to melt the wax
 - heat water to 95 °C and stir in
 - stir in SILLITIN N 85 PURISS and let cool down

- Suppliers**
- (1) Clariant
 - (2) ExxonMobil
 - (3) Wacker
 - (4) HOFFMANN MINERAL

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.