



## AUTOMOTIVE INDUSTRY

### Car polish LP 40, with solvents

Basis: Wacker		RR 005
Wacker E 32	(1)	4.0
Wacker E 1044	(1)	1.0
Wacker E 10	(1)	1.0
Carbopol EZ 2	(2)	0.3
SILLITIN N 85 PURISS	(3)	5.0
Shellsol T	(4)	5.0
White spirit 100-140 °C		10.0
Water, softened		73.4
Triethanolamine		0.2
Preservative		(as needed) 0.1
Total parts by weight		100.0

- Mixing**
- disperse Carbopol EZ 2 in water at room temperature
  - stir in one after another Wacker E 32, Wacker E 1044, Wacker E 10, SILLITIN N 85 PURISS, white spirit, Shellsol T, triethanolamine and the preservative

- Suppliers**
- (1) Wacker
  - (2) Lubrizol
  - (3) HOFFMANN MINERAL
  - (4) Shell Chemicals

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.