



**AUTOMOTIVE INDUSTRY**  
**Car polish LP 62, with solvents**  
**creamy, very easy to rub off**

Basis: Wacker		RR 007
Wacker E 1044	(1)	2.5
Wacker AK 100	(1)	1.5
Carbopol EZ 2	(2)	0.1
SILLITIN N 85	(3)	3.0
Shellsol T	(4)	5.0
White spirit 100-140 °C		5.0
Water, softened		82.8
Triethanolamine		0.1
Preservative		as needed
Total % by weight		100.0

- Mixing**
- disperse Carbopol EZ 2 in water at room temperature
  - stir in Wacker E 1044 and the mixture of Wacker AK 100, Shellsol T and white spirit
  - then stir in SILLITIN N 85 and triethanolamine

- Suppliers**
- (1) Wacker
  - (2) Lubrizol
  - (3) HOFFMANN MINERAL
  - (4) Shell Chemicals

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.