



AUTOMOTIVE INDUSTRY
Car polish, solvent-free
with carnauba wax

		RR 008
Water, softened		59.8
Kahlwax self-gloss wax 2090	(1)	3.0
Wacker E 1656	(2)	8.0
Wacker E 1044	(2)	20.0
SILLITIN Z 86 PURISS	(3)	9.0
Preservative		(as needed) 0.2
Total % by weight		100.0

- Mixing**
- heat water up to 95 °C
 - sprinkle Carnauba self-gloss wax 2090 while stirring and dissolve
 - let cool down to 40 °C
 - stir in Wacker E 1656, Wacker E 1044, SILLITIN Z 86 PURISS and the preservative

- Suppliers**
- (1) Kahl
 - (2) Wacker
 - (3) HOFFMANN MINERAL

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.