



AUTOMOTIVE INDUSTRY
Car polish LP 66, solvent-free
overpaintable

Basis: Wacker		RR 009
Wacker TNE 50	(1)	3.0
Wacker E 32	(1)	1.0
Carbopol EZ 2	(2)	0.3
SILLITIN Z 86	(3)	5.0
Water, softened		90.5
Triethanolamine		0.2
Preservative		as needed
Total % by weight		100.0

- Mixing**
- disperse Carbopol EZ 2 in water at room temperature
 - stir in the other ingredients

- Suppliers**
- (1) Wacker
 - (2) Lubrizol
 - (3) HOFFMANN MINERAL

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.