

**AUTOMOTIVE INDUSTRY****Antifogging agent AB 15, solvent-free
good cleaning of glass surfaces**

Basis: Wacker		RR 012
Wacker L 053	(1)	4.0
Carbopol EZ 2	(2)	0.3
SILLITIN N 85	(3)	5.0
Water, softened		90.5
Triethanolamine		0.2
Preservative		as needed
Total % by weight		100.0

- Mixing**
- disperse Carbopol EZ 2 in water at room temperature
 - stir in the other ingredients one after another

- Suppliers**
- (1) Wacker
 - (2) Lubrizol
 - (3) HOFFMANN MINERAL

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.