



AUTOMOTIVE INDUSTRY

Car polish, solvent-free

Basis: Clariant		RR 022
Licowax KSL	(1)	4.0
Water, softened		82.1
Genapol OX 070	(1)	1.5
Kelzan S	(2)	0.3
Wacker AK 350	(3)	6.0
SILLITIN N 85 PURISS	(4)	6.0
Preservative		(as needed) 0.1
Total % by weight		100.0

- Mixing**
- heat Licowax KSL, Genapol OX 070 and Wacker AK 350 to 90 °C to melt the wax
 - heat water to 90 °C and stir in
 - stir in Kelzan S and SILLITIN N 85 PURISS
 - let cool down to approx. 30 °C while stirring and add preservative

- Suppliers**
- (1) Clariant
 - (2) CP Kelco
 - (3) Wacker
 - (4) HOFFMANN MINERAL

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.