



AUTOMOTIVE INDUSTRY

Car conditioning cream

		RR 026
Licowax LP	(1)	5.0
Stearic acid		2.0
Wacker AK 1000	(2)	7.0
Tego Polish Additiv C 3191	(3)	2.0
Exxsol D 80	(4)	15.0
Brij S721	(5)	0.5
Brij S2	(5)	0.5
SILLITIN Z 86 PURISS	(6)	8.0
Water, softened		60.0
Preservative		as needed
Total % by weight		100.0

- Mixing**
- heat Licowax LP, stearic acid, Wacker AK 1000, Tego Polish Additiv C 3191, Exxsol D 80, Brij S721 and Brij S2 to 90 °C to melt the wax
 - heat water to 95 °C and stir in
 - stir in SILLITIN Z 86 PURISS

- Suppliers**
- (1) Clariant
 - (2) Wacker
 - (3) Evonik Industries
 - (4) ExxonMobil
 - (5) Croda
 - (6) HOFFMANN MINERAL

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.