

**AUTOMOTIVE INDUSTRY****Car polish, with solvents
detergent resistant**

Basis: Evonik Industries		RR 027
Carnauba wax		2.0
White spirit, aromatic-free		15.0
Tego Polish Additiv ACS	(1)	10.0
Wacker AK 350	(2)	5.0
Water		63.0
SILLITIN N 85 PURISS	(3)	5.0
Preservative		as needed
Total % by weight		100.0

- Mixing**
- solve the wax in warm white spirit
 - stir in the other ingredients in the given sequence until emulsified

- Suppliers**
- (1) Evonik Industries
 - (2) Wacker
 - (3) HOFFMANN MINERAL

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.