



AUTOMOTIVE INDUSTRY

Car polish, solvent-free detergent resistant

Basis: Evonik Industries		RR 028
Tagat S	(1)	3.6
Water, demineralized		10.0
Licowax S	(2)	4.0
Feruwax 64/66	(3)	2.0
Tegin M	(1)	1.8
Wacker AK 350	(4)	5.0
Tego Polish Additiv C 3191	(1)	3.0
Water, demineralized		70.4
Sodium chloride		0.2
SILLITIN N 85 PURISS	(5)	as needed
Preservative		as needed
Total % by weight		100,0

- Mixing**
- heat Tagat S and water and stir until homogeneous
 - melt Licowax S and Feruwax 64/66 with Tegin M and incorporate
 - add Wacker AK 350 and Tego Polish Additiv and homogenize well
 - add hot water with sodium chloride and cool down immediately

- Suppliers**
- (1) Evonik Industries
 - (2) Clariant
 - (3) Paramelt
 - (4) Wacker
 - (5) HOFFMANN MINERAL

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.