



OTHER APPLICATION

Molding, light-colored

Shoe sole, color neutral, oil resistant, flame retardant

70 Shore A, NBR, sulfur cure

Guide formulation of Azienda Chimica Milanese	SS 9/91
Perbunan 3307)*	100
Zinkoxyd aktiv	5
ImerFlex T10	40
SILFIT Z 91	40
Flectol H)**	1
Si 69	1.6
Hansa Dis T4	5
CBS	1.3
TMTD	0.3
Sulfur	1.5
Total phr	195.7

-)* No longer available. Recommended:
Standard product: Perbunan 3445 F
for potable water, food or low mold fouling: Perbunan 3446 F
-)** No longer available. Recommended: Vulkanox HS/LG

Mechanical properties

Density	g/cm ³	1.30
Tensile strength	MPa	12.0
Elongation at break	%	400
Hardness	Shore A	70
Abrasion	mm ³	180

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.