



OTHER APPLICATION

Molding, black

Shoe heel

85-90 Shore A, SBR, sulfur cure

Guide formulation of Azienda Chimica Milanese	SS 22/82 B
SBR 1502	70
Buna CIS 132-Schkopau	15
Europrene SOL B 1205	15
Zinkoxyd aktiv	3
Stearic acid	1
Ultrasil VN 3	50
SILLITIN Z 86	20
Hansa Dis T4	12
Si 69	2
Vulkanox SP	1.5
Antilux 110	0.5
Carbomix 1608)*	8
CBS	1.7
Rhenocure Thiuram MS	0.3
Sulfur	1.75
Total phr	201.75

)* No longer available. Recommended: SBR 4684

Mechanical properties

Density	g/cm ³	1.27
Tensile strength	MPa	14.0
Elongation at break	%	640
Hardness	Shore A	85-90
Abrasion	mm ³	80

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.