



## BUILDING INDUSTRY

### Flooring, light-colored

#### Antistatic, flame retardant

85 Shore A, NBR/PVC, sulfur cure

Guide formulation of Azienda Chimica Milanese Archive	AT129/17
Europrene OZO N 7033	100
Ebrosil SA 60	70
AKTISIL PF 216	70
Hansa Dis T4	15
Zinkoxyd aktiv	5
Titanium dioxide	4
CBS	1
TMTM	0.2
TESPT	1
Vulkanox SP	1
Sulfur	1.7
Total phr	268.9

#### Mechanical properties

Density		g/cm <sup>3</sup>	1.48
Tensile strength		MPa	15.0
Elongation at break		%	243
Hardness		Shore A	85
Abrasion		mm <sup>3</sup>	193
Compression set, 22 h @ 70°C	ASTM, B	%	40

#### Note

- Flame retard class C
- Antistatic 200 MΩ/m
- Resistant to acids and bases

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.