



## MACHINERY and EQUIPMENT

### Roller cover, black

80 Shore A, NR, sulfur cure

Guide formulation of Azienda Chimica Milanese Archive	AT11/19
Ribbed Smoked Sheets RSS1	100
Zinkoxyd aktiv	3
Stearic acid	1
AKTISIL PF 216	100
Hansa Dis T4	10
Carbon Black SRF	3
Vulkanox 4010 NA	1.5
MBTS	0.8
DPG	0.4
Sulfur	2.3
Total phr	222.0

### Mechanical properties

#### Cure 6 min @ 150°C

Density	g/cm <sup>3</sup>	1.34
Tensile strength	MPa	15.0
Modulus 300 %	MPa	7.3
Elongation at break	%	475
Tear resistance	N/mm	36
Hardness	Shore A	78
Rebound	%	50
Abrasion	mm <sup>3</sup>	150

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.