



CONSTRUCTION INDUSTRY

Profile, solid, light-colored

Building profile

60 Shore A, EPDM, peroxide cure / LCM cure

Guide formulation of Exxon		RRS 1
Vistalon 7500		100
SILLITIN P 87		100
Perkasil KS 300		30
Grundöl AP/E Core 600 (ex Flexon 876)		60
Titanium dioxide		20
Silquest A-172NT		2
PEG 4000		2
Zinc oxide		10
Caloxol W3		10
TAC		2
Perkadox 14-40		8
Total phr		344
Density	g/cm ³	1.35
ODR, ± 5°, 180°C		
ML, minimum	dNm	12.4
MH, maximum	dNm	100.5
ts ₂	min	1.0
tC ₉₀	min	6.3
Physical properties		
Press cure 8 min @ 180°C		
Hardness	Shore A	62
Modulus 100 %	MPa	2.5
Tensile strength	MPa	7.6
Elongation at break	%	270
Compression set		
Press cure 10 min @ 180°C		
24 h @ 100°C	ASTM B	%
24 h @ -25°C	ASTM B	%

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.