



## High quality facade paint, solvent-based scrub resistant

**Basis** Vinyltoluene / Acrylate

			F 20102.0 [1]
Pliolite VTAC-H	(1)		7.5
Pliolite AC3-H	(1)		3.0
Chlorinated paraffin 40 %			4.0
Chlorinated paraffin 70 %			3.5
Sojalecithin	(2)		0.5
White spirit			15.0
Shellsol A 100	(3)		15.0
Aerosil 200	(4)		0.3
Kronos 2300	(5)		20.0
Micro Mica	(6)		7.0
Plastorit 00	(7)		4.2
Millicarb	(6)		8.0
SILLITIN Z 89	(8)		12.0
Total % by weight			100.0

**Note** A 10 kg batch of this formulation was dispersed in a dissolver for 30 min.  
The viscosity has been adjusted to 160-170 s (4 mm flow cup, DIN EN ISO 2431) by adding white spirit.

<b>Technical Data</b>	Adhesion	DIN EN ISO 2409	cross cut 0
	Scrub resistance	after 10000 scrub cycles	no surface damage
	Outside weathering	after 9 months	okay

**Suppliers**

- (1) Omnova Solutions
- (2) Overlack
- (3) Shell Chemicals
- (4) Evonik Industries
- (5) Kronos International
- (6) Omya
- (7) Imerys Talc
- (8) HOFFMANN MINERAL

### **More information on this topic:**

[Filler Comparison in Solvent-based Facade Paints](#)

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.