



Facade paint

Silicate paint, water-based

Basis	Silicate		
	Guide Formulation of Woellner		F 14401.0 [1]
Component A	Omyacarb 2 GU	(1)	30.0
	SILLITIN N 85	(2)	20.0
	Tylose H 15000 YP2	(3)	0.2
	Kronos 2056	(4)	3.0
	Zinc oxide		11.5
	Lithopone 30 % L	(5)	6.0
	Quartz flour		10.0
	Omyacarb 10 GU	(1)	9.1
	Barium sulfate		10.0
		Total parts by weight	
Component B	Betolin K 35	(6)	71.3
	Demineralized water		28.4
	Glycerin		0.3
		Total parts by weight	
Mixing	mix component A and B (ratio 3:1) and let swell		
Suppliers	(1) Omya (2) HOFFMANN MINERAL (3) SE Tylose (4) Kronos International (5) Venator Materials Corporation (6) Woellner		

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.