



Industrial coating
UV-curing transparent primer for wood, highly reactive
TSCA-approved
without reactive diluent

Basis Polyether acrylate

Basis: Guide Formulation 4054/5a E (March 1994) of BASF		I 45402.0 [1]
Laromer PO 94 F	(1)	90.0
AKTISIL MAM	(2)	7.5
Talkum AT 1)*	(3)	2.5
Omnirad 500	(4)	3.0
Total parts by weight		103.0

)* Talkum AT 1 is no longer available
 Recommended: Finntalc M15

Technical Data

Viscosity	23°C, DIN 4 mm flow cup	approx. 90-120 s
Reactivity	approx. 20 g/m ²	approx. 20 m/min 1 lamp 120 W/cm

Suppliers

- (1) BASF
- (2) HOFFMANN MINERAL
- (3) Omya
- (4) IGM Resins
- (5) Elementis

More information on this topic:

[Neuburg Siliceous Earth in UV-Curing Wood Coatings \(Transparent Primer\)](#)

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.