



Industrial coating
UV-curing transparent surfacer for wood
without reactive diluent

Basis Polyether acrylate

Basis: Guide Formulation 7.8-4071/10 (April 1994) of BASF		I 45406.0 [1]
Laromer PO 94 F	(1)	30.0
AKTISIL MAM	(2)	22.0
Casonic DH 50/45 BrillantWeiss (CaSO ₄)	(3)	45.0
Soja-Lecithin STA conc.	(4)	0.5
Omnirad TPO	(5)	1.0
Omnirad BDK	(5)	1.5
Total % by weight		100.0

Technical Data

Consistency		paste
Reactivity	40-60 g/m ²	approx. 10-20 m/min 1 lamp 120 W/cm

Suppliers

- (1) BASF
- (2) HOFFMANN MINERAL
- (3) VG Orth
- (4) Lubrizol Coating Additives
- (5) IGM Resins

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.