



Industrial coating
UV-curing clear coat for wood, matte
high abrasion resistance

Basis Urethane acrylate

I 45411.2 [5]

Ebecryl 294/25 HD	(1)	65.0
HDDA	(1)	30.0
Benzofenone	(2)	3.0
Omnirad 1173	(3)	2.0
Byk-088	(4)	0.3
AKTISIL MAM	(5)	25.0
Total parts by weight		125.3

Technical Data

Gloss 60° (20 µm)	GU	57
Abrasion loss (Taber, S42 / 0.5 kg / 100 rev.)	mm ³	71

Reactivity approx. 15 m/min
1 lamp 80 W/cm

Suppliers

- (1) Allnex
- (2) Lamberti
- (3) IGM Resins
- (4) Byk Chemie
- (5) HOFFMANN MINERAL

More information on this topic:

[Neuburg Siliceous Earth in UV Curing Wood Coatings \(Surfacer and Top Coat\)](#)

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.