



Painting material
Rust converter, water-based
Primer for corroded steel

Basis Vinyl acrylate

		R 10102.2 [23]
Component A	Demineralized water	18.37
	Agitan DF 6420 (1)	0.20
	Kelzan S (2)	0.20
	Ammonia 25 %	0.01
Component B	Tannin	4.04
	Demineralized water	4.05
Component C	Dowfax 2A1 (3)	0.15
	SILLITIN Z 86 (4)	15.30
Component D	Butyl glycol	2.22
	Haloflex 202 (5)	55.46
Total % by weight		100.00

Mixing

- charge component A
- dissolve component B
- add and disperse component C
- complete by component D

Technical Data Viscosity (20°C, DIN 4 mm flow cup) approx. 25 s

Suppliers

- (1) Münzing Chemie
- (2) CP Kelco
- (3) Dow Chemical Company
- (4) HOFFMANN MINERAL
- (5) DSM NeoResins

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.