



Industrial coating Transparent wood filler

Basis Acrylate

Guide Formulation of Alberdingk Boley		FP 31/6
Butylcellosolve (BG)	(1)	5.0
Deionized water		20.9
Tego Dispers 750 W	(2)	3.0
SILLITIN Z 89	(3)	15.0
Mistron 754	(4)	5.0
Alberdingk AC 31	(5)	50.0
Byk-024	(6)	0.5
Rheovis PU 1214 NC	(1)	0.6
Total parts by weight		100.0

Mixing

- premix Butylcellosolve, water and Tego Dispers 750 W
- add SILLITIN Z 89 and Mistron 754, stir with high shear force for 20 min
- complete by remaining components

Suppliers

- (1) BASF
- (2) Evonik Tego Chemie
- (3) HOFFMANN MINERAL
- (4) Imerys Talc
- (5) Alberdingk Boley
- (6) Byk Chemie

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.