



Industrial coating
Coating for plastics, white, sprayable
for all kind of plastic parts

Basis Polyurethane

			K 20101.2 [13]
Component A	Shellsol A 100	(1)	12.90
	Ethyl acetate		12.90
	Desmolac 4340 X/iB	(2)	28.22
	Disperbyk-130	(3)	0.29
	CP 343-1 solution (20 % in Shellsol A 100)	(4)	5.88
Component B	Kronos 2310	(5)	11.10
	SILLITIN Z 89 PURISS)*	(6)	1.65
Component C	Nappar 6	(7)	10.70
	Isopropanol		16.36
Total % by weight			100.00

)* or AKTISIL PF 777 for improved adhesion

Mixing

- charge component A
- add and disperse component B
- complete by component C

Technical Data Density 0.94 g/cm³

Suppliers

- (1) Shell Chemicals
- (2) Covestro
- (3) Byk Chemie
- (4) Eastman Chemical Company
- (5) Kronos International
- (6) HOFFMANN MINERAL
- (7) ExxonMobil

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.