



Industrial coating

Anti-corrosion primer for high requirements
very high solid, VOC 250 g/l, good acid resistance
for non-sagging thick film applications

Basis Epoxy resin (bisphenol A + bisphenol A/F and polyamidoamine adduct)

			R 24403 D
Component A	Araldite GZ 7071 X 75	(1)	130.87
	Araldite GY 783	(1)	98.15
	Luvotix P 25 X	(2)	1.00
	n-Butanol		40.00
	Byk-057	(3)	3.50
	Zinkphosphat ZP 10	(4)	53.90
	Bayferrox 222	(5)	35.90
	AKTISIL PF 777	(6)	212.33
Component B	Shellsol A 100	(7)	39.10
	Aradur 450	(1)	81.20
Total parts by weight			695.95

Mixing The preparation of component A was realized by dissolver with adapted bead mill after predispersion by grinding (20 min, 7.8 m/s).
 Before adding pigment and filler, the liquid parts of component A are premixed for 5 min (using a part of the grinding beads). For activating Luvotix, the temperature of the mill base should exceed 55°C.

Application Spraying by air pressure, single-layered with a dry film thickness of 250 µm on cold-rolled steel (Sa 2½, sandblasted medium (G) according to ISO 8503-1)

Technical Data	Solids content (m/m)	%	85
	PVC	%	29
	VOC	g/l	250



Control with
talc and barite

R 24403 D
with
AKTISIL PF 777

Properties

Fineness of grind	µm	20	15
Sedimentation component A 28 d, 50°C		<i>a lot of, hard</i>	none
Dynamic viscosity A+B 0.1 s ⁻¹ , 23°C	Pa·s	10.2	173
Dynamic viscosity A+B 1000 s ⁻¹ , 23°C	Pa·s	2.4	1.5
Pot life (viscosity doubled)	min	50	160
Pendulum hardness after 336 h	s	76	93
Cross-cut test (3 mm after tape tear-off)		0	0-1
Abrasion loss	mg	253	156

Salt spray test DIN EN ISO 9227 NSS, 4000 h

Rating according to DIN EN ISO 4628 part 2-5 and 8

Degree of blistering		0	0
Degree of rusting		0	0
Degree of cracking		0	0
Degree of flaking		0	0
Degree of corrosion around a scribe	mm	< 0.3	< 0.3
Degree of delamination around a scribe	mm	34	22
Cross-cut test (3 mm after tape tear-off)		0-1	1

Humidity test DIN EN ISO 6270-2 CH, 2000 h

Rating according to DIN EN ISO 4628 part 2-5 and 8

Degree of blistering		0	0
Degree of rusting		0	0
Degree of cracking		0	0
Degree of flaking		0	0
Degree of corrosion around a scribe	mm	0.4	0.0
Degree of delamination around a scribe	mm	<i>not evaluated</i>	not evaluated
Cross-cut test (3 mm after tape tear-off)		0-1	1


Chemical resistance DIN EN ISO 2812-1

Rating according to DIN EN ISO 4628 part 2

10 % sulfuric acid, 23°C	1000 h	5 (S5)	0
10 % acetic acid, 23°C	168 h	3-4 (S4)	3 (S2) 30 %*

* To improve the resistance to organic acids, a cycloaliphatic hardener based on IPD is recommended, whereby results comparable to aromatic amine hardeners can be attained:

10 % acetic acid, 23°C	168 h	0	0
	760 h	4 (S4)	0



Suppliers

- (1) Huntsman Advanced Materials
- (2) Lehmann & Voss
- (3) Byk Chemie
- (4) Heubach
- (5) Lanxess
- (6) HOFFMANN MINERAL
- (7) Shell Chemicals

More information on this topic:

[Neuburg Siliceous Earth in High Solid Epoxy Coatings](#)

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.